Dear Author,

Please correct your galley proofs carefully and return them no more than four days after the page proofs have been received.

Please limit corrections to errors already in the text; cost incurred for any further changes or additions will be charged to the author, unless such changes have been agreed upon by the editor.

The editors reserve the right to publish your article without your corrections if the proofs do not arrive in time.

Note that the author is liable for damages arising from incorrect statements, including misprints.

Please note any queries that require your attention. These are indicated with a Q in the PDF and a question at the end of the document.

Reprints may be ordered by filling out the accompanying form.

Return the reprint order form by fax or by e-mail with the corrected proofs, to Wiley-VCH : advtherap@wiley.com

Corrections should be made directly in the PDF file using the PDF annotation tools. If you have questions about this, please contact the editorial office. The corrected PDF and any accompanying files should be uploaded to the journal's Editorial Manager site.

To avoid commonly occurring errors, **please ensure that the following important items are correct** in your proofs (please note that once your article is published online, no further corrections can be made):

- **Names** of all authors present and spelled correctly
- **Titles** of authors correct (Prof. or Dr. only; please note, Prof. Dr. is not used in the journals)
- **Addresses** and **postcodes** correct
- **E-mail address** of corresponding author correct (current email address)
- **Funding bodies** included and grant numbers accurate
- **Title** of article OK
- All **figures** included
- **Equations** correct (symbols and sub/superscripts)

Author Query Form

Journal ADTP
Article adtp201800038

Dear Author,

During the copyediting of your manuscript the following queries arose.

Please refer to the query reference callout numbers in the page proofs and respond to each by marking the necessary comments using the PDF annotation tools.

Please remember illegible or unclear comments and corrections may delay publication.

Many thanks for your assistance.

Query No.	Description	Remarks
Q1	Author: Please provide GToC Keyword.	
Q2	Author: Please confirm that forenames/given names (blue) and surnames/family names (vermilion) have been identified correctly.	
Q3	Author: Kindly provide the complete postal address along with the postal code for all affiliations.	
Q5	Author: Please limit the biography of "Fergal J. O'Brien" to 100 words.	
Q6	Author: Please check the sentence "This clinical trial resulted....diagnosed distal non-union," for clarity.	
Q7	Author: Please confirm whether "mothers against" is appropriate as given.	
Q8	Author: Please clarify the sentence "The pathology of ... and progression of this disease."	
Q9	Author: The sentence "Another anti-inflammatory...in an arthritic mouse knee," has been reworded for clarity. Please check.	
Q10	Author: Please check the sentence "In order to enhance...delivery of BMP-2 alone," for clarity.	
Q11	Author: Please check whether "grow factor supplementation" should be changed to "growth factor supplementation."	
Q12	Author: Please check keywords as typeset for correctness.	
Q13	Author: Ref. 1 has been modified to include the names of the first 30 authors. Please check and confirm if the changes made are accurate.	
Q14	Author: Please provide the missing volume number in refs. 204, 236, 249, and 252.	
Q15	Author: Please provide the page number in refs. 35, 73, 76, 105, 138, 170, 325, and 331 if now available.	
Q16	Author: Please provide volume/page numbers in refs. 104, 111, 114, and 340 if now available.	

Q17	Author: Please provide complete information for refs. 41, 45, 155, 245, and 252.	
Q18	Author: Please provide the missing year in ref. 292.	

Author: Please confirm that Funding Information has been fied correctly.

Please confirm that the funding sponsor list below was correctly extracted from your article: that it includes all funders and that the text has been matched to the correct FundRef Registry organization names. If a name was not found in the FundRef registry, it may not be the canonical name form, it may be a program name rather than an organization name, or it may be an organization not yet included in FundRef Registry. If you know of another name form or a parent organization name for a “not found” item on this list below, please share that information.

FundRef Name	FundRef Organization Name
Science Foundation Ireland	Science Foundation Ireland
Advanced Materials and Bioengineering Research (AMBER) centre	
Investigator Programme grant	
European Research Council	European Research Council

T. Gonzalez-Fernandez, D. J. Kelly, F. J. O'Brien* 1800038

Controlled Non-Viral Gene Delivery in Cartilage and Bone Repair: Current Strategies and Future Directions

Controlled gene delivery for musculoskeletal regeneration depends on a multifactorial design in which the choice of gene delivery method, therapeutic gene, and supportive biomaterial play a central role for the success of this strategy. This article reviews the different modalities of non-viral gene delivery, gene targets, and their incorporation to biocompatible scaffolds for cartilage and bone repair.

Controlled Non-Viral Gene Delivery in Cartilage and Bone Repair: Current Strategies and Future Directions

Tomas Gonzalez-Fernandez, Daniel J. Kelly, and Fergal J. O'Brien*

Recent advances in the approval and commercialization of gene therapeutics have fostered the return of gene therapy to center stage. But despite new optimism, no Food and Drug Administration approved product exists for the treatment of orthopedic disorders. Non-viral gene delivery is a promising alternative to recombinant protein administration and viral gene transduction for orthopedic tissue engineering. When applied using appropriately designed systems, it enables temporal control of the overexpression of therapeutic genes, leading to local production of regulatory factors at physiologically relevant levels. Incorporating genetic material into 3D scaffold biomaterials, that is, gene activated scaffolds or hydrogels, presents a particular opportunity to utilize non-viral gene therapy for in situ transfection of host cells and the regeneration of damaged tissues and organs. But controlled non-viral gene delivery for musculoskeletal regeneration depends on a multifactorial design in which the choice of gene delivery method, therapeutic gene, and supportive biomaterial play a central role for the success of this strategy. This paper reviews the different modalities of non-viral gene delivery used for the repair of bone and cartilage, and explores the current challenges and opportunities for the engineering of functional orthopedic tissues using gene activated scaffolds.

million people in the United States reported musculoskeletal conditions, resulting in 21 million hospital admissions and 2.1 billion drug prescriptions, with an economic impact of \$796.3 billion.^[4]

The ability of the skeletal system to self-repair varies considerably between tissues. While long bones are one of the few organs in the human body with the ability to regenerate spontaneously, large segmental defects and voids may fail to heal by themselves.^[5] Delayed or impaired healing is estimated to occur in 5–10% of bone fractures accounted annually in the United States, and up to 10% of all fractures will require additional surgical procedures due to impaired healing.^[6,7] Articular cartilage has a very limited capacity to self-regenerate, and when left untreated, cartilage defects can progress to osteoarthritis (OA),^[8] the most common joint chronic disorder and a leading cause of disability.^[9,10]

1. Introduction

1.1. Burden of Musculoskeletal Disorders

Musculoskeletal disorders are one of the leading causes of disability.^[1] They have been identified as the most important contributor to the "years lived with disability" (YLD) indicator globally,^[1,2] accounting for 6.8% of total disability-adjusted life years, increasing by 45% during the period 1990–2011.^[3] The substantial increase in the prevalence of musculoskeletal diseases represents a huge economic burden in the national health care systems of developed countries. In 2011, more than 102

1.2. Tissue Engineering and Regenerative Medicine for the Musculoskeletal System

Due to the limitations of current surgical procedures, significant progress has been made in the field of tissue engineering and regenerative medicine (TERM) to enhance the repair and regeneration of injured and diseased musculoskeletal tissues. The market for regenerative medicine products for bone and joint applications is estimated to grow from \$2.9 billion in 2015 to nearly \$4.1 billion in 2020.^[11] TERM strategies have been traditionally based on the combination of three factors (also known as the tissue engineering triad): 1) cells, 2) supportive biomaterials, and 3) bioactive factors to direct repair and/or engineer a desired tissue type

Dr. T. Gonzalez-Fernandez, Prof. D. J. Kelly, Prof. F. J. O'Brien
Trinity Centre for Bioengineering
Trinity Biomedical Sciences Institute
Trinity College Dublin
E-mail: fjobrien@rcsi.ie

Dr. T. Gonzalez-Fernandez, Prof. D. J. Kelly, Prof. F. J. O'Brien
Department of Mechanical and Manufacturing Engineering
School of Engineering
Trinity College Dublin

Dr. T. Gonzalez-Fernandez, Prof. D. J. Kelly, Prof. F. J. O'Brien
Advanced Materials and Bioengineering Research Centre
Trinity College Dublin and Royal College of Surgeons in Ireland

Dr. T. Gonzalez-Fernandez, Prof. F. J. O'Brien
Tissue Engineering Research Group
Department of Anatomy
Royal College of Surgeons in Ireland

The ORCID identification number(s) for the author(s) of this article can be found under <https://doi.org/10.1002/adtp.201800038>

DOI: 10.1002/adtp.201800038

Tomas Gonzalez-Fernandez, after obtaining his bachelor's degree in biotechnology at Universidad Francisco de Vitoria (Spain) and Athlone Institute of Technology (Ireland), began his Ph.D. on "Integrating non-viral gene therapy and 3D bioprinting for bone, cartilage and osteochondral tissue engineering" as part of the Advanced Materials and Bioengineering Research Centre in Trinity College Dublin (Ireland).

Since completing his Ph.D. in 2018, he is currently working as a postdoctoral researcher in University of California, Davis (United States). His main research interest is the incorporation of protein and gene delivery into biofabrication technologies for the regeneration of bone and cartilage.

Daniel Kelly is the professor of tissue engineering and director of the Trinity Centre for Bioengineering in Trinity College Dublin. His research focuses on developing novel tissue engineering and 3D bioprinting strategies to regenerate damaged and diseased musculoskeletal tissues.

Fergal J. O'Brien is chair of Bioengineering and Regenerative Medicine and head of the Tissue Engineering Research Group in RCSI and a PI and deputy director of the Advanced Materials and Bioengineering Research Centre. He is a leading innovator in the development of advanced biomaterials for regenerative medicine. He is a member of the World Council of Biomechanics and

has served as Biomaterials Topic Chair for the Orthopedic Research Society and as an EU Council Member of TERMIS. His research focuses on the development and clinical translation of scaffold-based therapeutics for tissue engineering, with a major focus on functionalizing these scaffolds as systems to deliver biomedicines.

for implantation. However, despite significant recent progress in biomaterial science, cell therapy, and growth factor administration, a major clinical need for advanced therapeutics to treat complex injuries still exists.

The use of bioactive signals in the form of morphogens such as recombinant growth factors is of particular importance in TERM, but the delivery of the appropriate factors in a controlled and sustained manner remains challenging. Due to the short half-life of recombinant proteins, fast clearance from the body and lower therapeutic efficacy in comparison with natural proteins,^[12–14] supra-physiological concentrations of these proteins are often required to exert a biological effect, which might impair tissue repair and cause off-target effects.^[15–17] For example, the use of bone morphogenetic proteins (BMPs) has raised safety concerns due to potential abnormal bone overgrowth, local and systemic toxicity, immunogenicity, osteoclastic activation, and cancer risks.^[17–19] The US Food and Drug Administration (FDA)-approved INFUSE bone graft, a collagen sponge soak loaded with recombinant human bone morphogenetic protein 2 (rhBMP-2), has been found to cause ectopic bone formation, cytotoxicity, renal problems and has been associated with cancer.^[17] Due to these limitations, controlled release systems based on non-covalent (surface adsorption, physical entrapment, affinity binding, and ionic complexation) or covalent (chemical conjugation) immobilization^[20,21] of proteins into carrier materials have been investigated. Despite research efforts in this space, many of the pre-existing challenges remain when using these systems. In addition, rapid release kinetics, low loading efficiencies, and difficulty achieving spatiotemporal control of different factors have hampered the success of these approaches. In comparison to the controlled release of proteins, gene therapy might provide a more elegant approach for inducing cell-mediated expression of desired regulatory factors in a physiological, localized, and temporally controlled manner (Figure 1).

1.3. Gene Therapy in Regenerative Medicine: Concept, Advantages, and Current Prospects

Gene therapy involves the introduction of exogenous genes into a cell in order to correct or replace a pre-existing gene or to modulate their expression in order to accomplish a desired effect.^[22] In the context of musculoskeletal tissue repair, gene transfer is a promising alternative to the delivery of recombinant growth factors since it allows for the sustained synthesis of one or more native proteins at the site of injury.^[23] Also, the local synthesis of gene products, with native conformation and true post-translational modifications, might have a superior biological effect than recombinant proteins produced industrially using prokaryotic organisms which, in many cases, show severe restrictions for successful heterologous protein production.^[23,24] Additionally, gene therapy for orthopedic tissue engineering (TE) also offers the possibility to deliver transcription factors, signaling molecules, and receptor proteins which are localized in specific cellular compartments.^[23] But most importantly, this technique could be a more physiological and compatible approach to promote wound healing and tissue repair.^[25]

Figure 1. Protein and gene delivery for repair of orthopedic tissues. The DNA is transcribed into RNA and then translated into a protein that can be delivered in vivo using a 3D matrix or direct injection to enhance tissue repair. The DNA sequence encoding for a gene of interest can also be cloned into a pDNA which can be delivered to cells in an ex vivo approach by viral and non-viral approaches. Either the pDNA or the transfected cells can also be delivered in vivo alternatively through either 3D biomaterials or direct injection to produce a therapeutic effect.

Since the 1980s the concept of using gene transfer to correct genetic disorders has been considered as a potential paradigm shift in medicine. However, although the first gene therapy trial to treat adenosine deaminase severe combined immunodeficiency (ADA-SCID) highlighted the potential of gene therapy for the treatment of monogenic diseases,^[26] later clinical trials for the treatment of ornithine transcarbamylase deficiency resulted in the death of one patient, and the development of T cell leukemic disease in 5 out of 20 treated infant patients, highlighting the safety risks associated with these approaches.^[27–29] These severe complications halted the clinical progress of the field and reduced the previous optimism that existed. Over the following two decades, the field of gene therapy has matured with more than 35 000 papers, 16 000 US patents, and 1800 clinical trials^[30] and the clinical approval of Glybera, involving an adeno-associated viral vector for delivery of the gene for lipoprotein lipase (LPL), as the first human gene therapy product approved for use in the West by the European Medicines Agency (EMA) in 2012^[31,32]

(Table 1). Despite the record-breaking price tag of Glybera^[32] (Table 1) and its withdrawal from the market after the successful treatment of a single patient, 2016 and 2017 have been notable years for the development of gene therapy^[33,34] (Table 1). FDA approval for two treatments, Kymriah and Yescarta, based on autologous implantation of genetically modified T-cells for the treatment of different types of cancer,^[35,36] and approval of Luxturna after restoring the vision of two dozen patients affected by an inherited genetic disease,^[37] together with clinical successes for the treatment of sickle-cell disease,^[38] epidermolysis bullosa,^[39] and hemophilia^[40] have precipitated the return of gene therapy to center stage and generated new optimism in the field. Furthermore, new FDA guidelines to speed the introduction of treatments involving human cells and tissues,^[41] including gene therapy, could accelerate the translation of cell and gene therapies and encourage the development of novel treatments and clinical trials.

Despite this promising progress, no FDA-approved product exists in orthopedic gene therapy and only a few products have

Table 1. Approved gene therapies for human treatment.^[42]

Product name	Indication	Gene product	Viral vector	Approval authority and year	Treatment cost per patient	Market availability
Gendicine	Head and neck carcinoma	p53	Adenovirus	People's Republic of China, 2003	USD360 per injection ^[43]	On the market
Glybera	Lipoprotein lipase deficiency	Lipoprotein lipase	Adeno-associated virus	EMA, 2012	USD1.4 million ^[44]	Discontinued
Imlygic	Melanoma	Granulocyte-macrophage colony-stimulating factor	Herpes simplex virus	EMA, FDA, 2012	USD65 000 ^[45]	On the market
Strimvelis	Adenosine deaminase	Adenosine deaminase	Retrovirus	EMA, 2016	USD710 000 ^[46]	On the market
Invossa	Osteoarthritis	Transforming growth factor- β 1	Retrovirus	South Korea, 2017 (July)	Not available	Not available
Kymriah	Acute lymphoblastic leukemia	Chimeric antigen receptor	Lentivirus	FDA, 2017 (August)	USD475 000 ^[47]	On the market
Yescarta	Large B-cell lymphoma	Chimeric antigen receptor	Lentivirus	FDA, 2017 (October)	USD373 000 ^[47]	On the market
Luxturna	Retinal dystrophy	RPE65 gene	Adeno-associated virus	FDA, 2017 (December)	USD425 000 ^[48]	On the market

been moved into clinical trials and completed phase II.^[49,50] More recently, a cell-mediated gene therapy for degenerative arthritis, Invossa, has been approved by South Korean regulators for the treatment of osteoarthritis by a single intra-articular injection of chondrocytes overexpressing transforming growth factor β 1 (TGF- β 1),^[51] and phase III trials are expected to begin in early 2018 in the United States under a special protocol assessment with the FDA.^[42]

This review summarizes the past and current efforts in the use of non-viral gene therapy for the regeneration of orthopedic tissues, focusing on its application to biomaterial-guided TE strategies and its potential for translation into the clinic to broaden the field of gene therapy from the treatment of rare genetic diseases to the point where it can impact the daily life of millions of people suffering from degenerative musculoskeletal disorders.

2. Gene Therapy in Orthopedic Tissue Engineering: Gene Activation of 3D Biomaterials for the Treatment of Musculoskeletal Injuries

Traditionally, the field of gene therapy has focused on the treatment of hereditary monogenic diseases. Most of the previously mentioned products approved for use in the 2012–2017 period, such as Luxturna and Strimvelis, are examples of this application (Table 1). In contrast, musculoskeletal TERM focuses on the treatment of complex traumatic injuries, such as non-union bone fractures and cartilage defects, and chronic diseases, such as osteoarthritis (OA), in which the systemic and permanent modification of a single gene is not required. Instead, regenerative approaches focus on promoting a local and multifactorial response to induce healing and de novo tissue formation. The rationale behind the use of gene therapy in TERM lies in providing therapeutic gene products to direct and promote repair at the site of injury until tissue homeostasis is re-established.

In this context, the functionalization of biomaterials to form gene activated (GA) scaffolds, also known as gene activated matrices, resulting from the incorporation of one or multiple genes of interest and its delivery vector into a biodegradable material which offers structural support, cell attachment, and retention

of new tissue formation, have been explored for confined gene delivery and in situ therapeutic outcomes. These platforms may provide a more prolonged delivery of the transgene, while localizing the effect of its overexpression, overcoming the limitations of in vitro 2D transfection^[52,53] and systemic or local injection which may not be appropriate for targeting a specific tissue and do not offer spatial confinement of the delivered genes^[54,55] (Figure 2). If such systems can effectively target host cells, they may be superior to ex vivo approaches in which the therapeutic effect is dependent on the survival of the transfected cells in the host following implantation.

The activation of biomaterials with therapeutic genes was initially developed by Fang et al. and Bonadio et al. in the 1990s as an inexpensive off-the-shelf alternative to protein and viral gene delivery for the repair of in vivo long bone defects.^[25,56] In these two studies, once implanted in the defect area, free pDNA loaded collagen sponges were colonized by the host cells, showing for the first time that repair cells could be transfected in vivo^[56] to continuously express the genes of interest resulting in a faster and reproducible healing of the damaged bone.^[25,56] Since these early innovative attempts, further research on GA scaffolds has focused on improving their DNA binding capabilities, their capacity to deliver the genes of interest and cell transfection, and their healing outcome.

In 2016, the world's first clinical trial with a non-viral gene activated scaffold consisting of a collagen-hydroxyapatite (HA) loaded with plasmid DNA (pDNA) encoding for the vascular endothelial growth factor (VEGF) targeting host cell transfection, was performed in Russia for maxillofacial reconstruction.^[57] This clinical trial resulted in no signs of adverse effects and, after 3 months post-implantation, and in new tissue formation of similar density to spongy bone on the site of a previously diagnosed distal non-union.^[57] More recently, in 2017, another clinical trial involving the co-delivery of pDNA encoding for BMP-2 and VEGF genes in a GA demineralized bone allograft for the treatment of ulnar pseudarthrosis, resulted in callus formation and pain reduction only 2 months after implantation.^[58] These promising results are encouraging for the use of biomaterial-guided gene delivery as a novel approach for the regeneration of damaged musculoskeletal tissues.

Figure 2. Local injection versus material-based administration of gene therapeutics. Gene activated materials can act as a depot for the gene of interest, allowing a localized delivery at the site of action.^[25] Also, the scaffold facilitates the infiltration of endogenous cells and subsequent cellular nucleic acid uptake, promoting tissue repair.^[25,56] In contrast, local injection can result in the diffusion of the gene therapeutic away from the site of action which can cause off-site adverse effects.^[54,55]

3. The Two Basic Components for a Successful Gene Activated Scaffold: Gene Delivery Vectors and Supportive Biomaterials

The ultimate therapeutic success of a GA scaffold approach, outside the choice of therapeutic gene, depends mainly on two factors: 1) the gene delivery vector which is going to allow for the efficient uptake and subsequent expression of the gene of interest by host or transplanted cells; and 2) the scaffold as a supportive material that contains the gene and its vector and which facilitates the cell–vector interaction, retains the expression products of the transgene and guide tissue regeneration.

3.1. Gene Delivery Vectors: Viral versus Non-Viral Gene Delivery in the Context of Tissue Regeneration

Gene delivery faces many cellular barriers that need to be overcome for the efficient expression of the gene of interest. Nucleic acids require effective cell uptake to pass through the cell membrane and cytoplasm and avoid degradation in order to arrive at the nucleus where the transcription takes place.^[59] A key component of gene therapy is the choice of the gene delivery vector, that is, the vehicle that can effectively deliver the DNA molecule encoding for the gene of interest to the target tissue or cell type, ensuring a suitable expression profile of the transgene. The principal division between gene delivery vectors is whether they are viral or non-viral (Table 2).

Non-viral gene delivery can be divided in physical (or vector free) and chemical. While physical transfection methods rely on the delivery of the pDNA through the temporal disruption of the cell membrane, chemical methods consist of the complexation of the pDNA to different types of macromolecules which protect the pDNA from degradation and facilitate its transport to the cell nucleus. Viral vectors are often classified according to their viral family, and their delivery mechanism is based on their inherent ability to translocate their own genetic material into the host's genome in a process known as transduction.

Viral vectors are preferred generally in gene therapies^[60] due to their high cell transfection efficiencies of around 80–100% (Table 2). More than 70% of gene therapy clinical trials carried out so far have used viral vectors.^[61] Also, all the gene therapies approved for use in human patients use viral gene delivery approaches (Table 1). The main concerns associated with viral vectors relate to their potential immunogenicity, the risk of insertional mutagenesis that can result in oncogene transactivation and leukemia, and difficulties in their production^[61,62] (Table 2). Despite the huge amount of work focused on the development of safer viral vectors over the last decade, safety concerns still prevail. Lentiviral (based on viruses of the family Retroviridae) and adenoviral (based on viruses of the family Adenoviridae) approaches have been developed for cartilage and bone regeneration, but their use in orthopedic TE is hindered by the difficulties of linking the viruses to 3D matrices for localized transfection.^[63–69] One approach to address this issue is to use chemical immobilization of viral vectors into 3D materials,^[64,66] which can provide spatial control of gene transfection in a mechanically functional scaffold. Another alternative

Table 2. Characteristics of viral and non-viral gene delivery vectors for their use in combination with 3D matrices.

Characteristics	Types of gene delivery vectors	
	Viral	Non-viral
Transfection efficiency of primary cells	High (80–100%) ^[64,73]	Low/moderate (1–40%) ^[74–76]
Transgene expression levels	High [ng mL ⁻¹] ^[64]	Moderate [pg–ng mL ⁻¹] ^[75–78]
Durability of expression	Persistent	Transient
Ease of production	Low	High
Ease of incorporation to 3D matrices	Low	High
Infectivity	Adenoviruses and lentiviruses infect dividing and non-dividing cells, retroviruses only infect dividing cells	Infect dividing and non-dividing cells
Safety	Insertional mutagenesis risk, immunogenicity	Cytotoxicity at high doses, non-infectious
Compatibility with regenerative processes	High expression of growth factors for long time periods can impair tissue healing and aggravate previous tissue pathologies	Low expression for shorter periods of time

is to adsorb the viruses into natural polymeric scaffolds, however this approach can lead to the leakage of the viral vector to the surrounding tissue.^[68] Also, recombinant adeno-associated viruses (rAAV) have been investigated for regenerative medicine as a promising viral vector to overcome the limitations associated with retroviruses and adenoviral vectors. These show reduced host immune response due to the removal of the immunogenic sequences in the viral genome and no risk of insertional mutagenesis as their genetic material is kept as an episome, similar to non-viral pDNA delivery.^[70,71] In addition, rAAV vectors have been combined with hydrogels for sustained gene transfection of stem cells, highlighting their potential for TE.^[72]

In comparison to the incorporation of viral gene delivery into biomaterials following a GA scaffold approach for in vivo transfection, ex vivo viral gene transduction of a desired cell type and posterior seeding of transfected cells in 3D constructs has been suggested as an easier and more successful approach. However, this depends on cell survival upon implantation. As an example of this approach in cartilage regeneration, the use of adenoviruses for the delivery of the chondrogenic factor sex determining region Y box 9 (SOX9)^[65] and BMP-2^[67] genes and subsequent incorporation of the transfected cells into polyglycolic acid (PGA) matrices has been shown to enhance the regeneration of large partial-thickness and full-thickness cartilage defects.

One of the main concerns of the use of viral vectors in orthopedic TE applications is the effect of the long-term overexpression of high levels of growth factors which might impair the regenerative and tissue repair processes (Figure 3). While the adenoviral delivery of TGF- β 1 through intra-articular administration into arthritic rabbit knee joints resulted in successful transgene overexpression, the high levels of transduction caused pathological changes in the knee and the surrounding muscle tissue stimulating cartilage degradation, muscle edema, and fibrogenesis instead of repair.^[79] These results suggest that more controlled transfection and transgene expression is preferable^[25,79] (Figure 3).

In comparison to viral gene delivery, non-viral approaches can be more advantageous for TERM due to temporal transfection, ease of production, safety, low immunogenicity,^[61] and ease of incorporation into 3D matrices (Table 2). The direct comparison of ex vivo liposomal and adenoviral BMP-2 delivery to bone marrow-

Figure 3. Schematic representation of the usual protein levels obtained by loading the protein into 3D matrices, viral gene delivery and non-viral gene delivery over time. Protein release kinetics from 3D constructs is limited by a quick release that occurs during the first few days of loading.^[25] Viral and non-viral gene delivery offers a more sustained and durable release.^[25] But, while viral transduction offers constant production of high levels of the transgene, non-viral transfection offers a temporally limited expression of lower transgene levels.^[81]

derived mesenchymal stem cells (BMSCs) showed that, while the adenoviral infected BMSCs promoted the formation of excessive and abnormal bone in vivo, liposome-based delivery resulted in repaired tissue more similar to the native bone in thickness and shape.^[80] These results highlight the potential of non-viral gene delivery as a more physiological approach for successful repair.

3.2. Gene Activated Biomaterials: Classes and Configuration

When applying gene therapy to TE we should consider that the scaffold should not only be biocompatible and allow for gene transfection, but also promote and maintain the desired phenotype and guide the formation of new tissue, approaching its native mechanical and biochemical properties. The choice of material for a GA scaffold must be specific for the desired tissue type and be optimized to promote the final goal of orthopedic tissue

repair. Based on these concepts, some of the necessary characteristics required for a GA biomaterial include:

- 1) Cell compatible to allow for cell survival, growth, and differentiation.
- 2) Facilitate nucleic acid–matrix interaction, to retain the gene of interest in the site of action and avoid its uncontrolled diffusion to the surrounding tissues.
- 3) Allow for cellular uptake of the gene of interest, facilitating transfection and specific protein production.
- 4) The material and its production mechanism should be chemically and physically compatible with the nucleic acid and its delivery vector to avoid damage of the genetic material and undesired interactions that might hinder transfection.
- 5) Adaptability of the material to be easily modified to allow for the desired release/up take kinetics and to be customized for different applications depending on the characteristics of the target tissue and injury type.
- 6) The material of choice must be biodegradable and bioabsorbable to guarantee integration with the surrounding tissue and to avoid interference with the natural healing processes.

Biodegradability and bioresorbability are essential parameters for tissue regeneration strategies in order to avoid inflammatory or foreign-body reactions that are likely to result in rejection and/or tissue necrosis.^[82] To couple both, mechanical integrity of the scaffold and the replacement of the scaffold with functional tissue, remains challenging in TE. While the biodegradation of synthetic polymers happens through passive hydrolysis and is determined by the molecular weight and concentration of the polymer, the degradation of natural polymers depends on enzymatic reactions.^[83] Enzymatic degradation can be controlled by various cross-linking processes, such as carbodiimide chemistry^[84] and glutaraldehyde,^[85] to increase the resistance of the material when implanted in vivo.

Taking these observations into account, different natural and synthetic materials in different conformations have been explored for material-guided gene delivery in orthopedic tissues.

3.2.1. Natural Polymers

Polymers of natural origin are a promising biomaterial class for TE due to their biocompatibility, biodegradability, and their biomimetic signaling that promotes cell migration, proliferation, and differentiation. Biopolymers can also be processed in a variety of ways to form different types of scaffolds, from porous constructs to hydrogels. Natural materials such as collagen, chitosan, calcium phosphate (CaP), fibrin, hyaluronic acid (HyA), and alginate among others have been used as GA scaffolds for non-viral gene delivery in the context of bone and cartilage TE. As the major component of extracellular matrix (ECM), collagen was the initial material used for GA material technology.^[25] Furthermore, the natural interactions between cells and collagen has been hypothesized to facilitate the cellular uptake of adsorbed pDNA and vector-pDNA complexes,^[86] and collagen's natural capacity to bind to cytokines might increase the retention of the overexpressed factors and maximize their therapeutic outcome. Porous collagen scaffolds have also been tailored in terms of mechanical

properties and chemical composition to direct MSC differentiation toward either the osteogenic or chondrogenic phenotype.^[87] For example, the gene activation of CaP modified collagen matrices have been shown to be superior for bone regeneration than when collagen-glycosaminoglycan (GAG) matrices were used.^[88] These studies highlight the importance of coupling both the matrix material and the gene delivery strategy to leverage the possible synergistic therapeutic effects.

3.2.2. Synthetic Polymers

Natural polymers face challenges such as batch-to-batch variability, immunogenicity, difficulty of sterilization, low mechanical properties, and poor control of the degradation rate and release kinetics.^[20] Synthetic polymers offer great versatility which allows for tailoring their physical, chemical, and mechanical properties for different TERM applications. Additionally, they allow for fine control of pore size, geometry, and connectivity for tunable controlled release of bioactive factors.^[20] Different synthetic polymers such as polycaprolactone (PCL), poly(lactide-co-glycolide) (PLG), poly(lactic-co-glycolic acid) (PLGA), and polyethyleneglycol (PEG) have been explored as substrates for non-viral gene delivery in orthopedic TE.^[89–92] However, a major limitation of synthetic polymers is facilitating appropriate cellular interaction. Functionalization of these materials with cell adhesion ligands or with ECM-derived materials has been investigated to increase cell interaction, differentiation, and specific tissue formation.

3.2.3. Material Configuration

In addition to the choice of material, its configuration is also important for use as GA scaffolds. Porous GA scaffolds are the main material configuration used as a platform for gene delivery. They are preferred due to the ease of pDNA loading and high cell motility which allows for continuous gene uptake. Gene activated hydrogels have also been developed due to their potential delivery via minimally invasive administration, high permeability for oxygen and nutrients, homogeneous cell and nucleic acid distribution, and their suitability for the treatment of irregular-shaped defects.^[55] In addition, they are suitable for their use as cell and gene carriers in biofabrication techniques such as 3D bioprinting. Two widely used hydrogels for cartilage and bone TE are agarose^[93] and alginate.^[94–96] Additionally, the incorporation of ECM molecules to different types of hydrogels such as HyA or collagen^[97] have been studied in order to mimic the biochemical composition of native tissues.

4. Non-Viral Gene Therapy Strategies for Musculoskeletal Tissue Engineering

While vector-free methods are based on the physical disruption of the cellular barriers allowing for the entry of the genetic material into the cell, the complexation of the nucleic materials in the form of pDNA to vectors of different chemical origin can facilitate nucleic acid uptake and effective cell transfection

Figure 4. Schematic of different non-viral gene delivery methods. While vector-free delivery is based on the physical disruption of the cell membrane for the introduction of the desired genetic material,^[98] the complexation of pDNA with vectors of inorganic,^[99] lipid,^[61] polymeric,^[61] and peptide^[100] origin facilitates interaction with the cellular membrane, the protection of the pDNA in the cell cytoplasm and nuclear delivery.

(Figure 4). The different strategies for non-viral gene delivery and their use in TERM are listed in this section, with particular focus on their combination with biomaterials and stem cells for tissue regeneration.

4.1. Vector Free

Vector-free methods include different types of cell membrane disruption approaches such as microinjection, needle injection, jet injection, pressurized DNA bombardment, high-voltage electrical currents like electroporation, sonoporation through ultrasound-mediated gene transfer, and hydrodynamic gene transfer using hydrostatic pressure.

While some of these techniques such as microinjection, DNA bombardment, and hydrodynamic gene transfer show limitations in orthopedic applications due to the high quantity of nucleic acid needed, lack of specificity, tissue and cell damage, and the need to transfect large cell populations,^[101] others have shown promise to deliver therapeutic genes to the musculoskeletal system in vivo^[102–106] and to progenitor cells in vitro for their use in ex vivo therapies^[107–110] (Table 3). Electropora-

tion has been successfully used for the introduction of therapeutic genes into MSCs to enhance their differentiation into the tenogenic,^[109] osteogenic,^[108] and chondrogenic^[107,110] phenotypes. Adipose stem cells (ASCs) transfected through electroporation with runt related transcription factor 2 (RUNX2) and osteon genes were able to promote bone formation subcutaneously in a nude mice model after 6 weeks in a PLGA scaffold.^[108] The same approach was used to promote in vivo cartilage formation by the electroporation of the SOX trio genes.^[107] Furthermore, electroporation of the TGF- β 3 genes showed superior levels of stem cell transfection in comparison to chemical vectors and enhanced chondrogenesis.^[110]

More recently, the use of ultrasound for gene delivery, also known as sonoporation, has been shown capable of transfecting cells in vivo and in vitro with pDNA that was previously loaded into a collagen scaffold in a model known as matrix-assisted sonoporation,^[105] allowing for very fine temporal control of the transfection. Two weeks after construct implantation on a minipig cranial and tibial defect, the application of ultrasound allowed for the transfection of 40% of the cells that colonized the construct and the expression of the BMP-6 transgene which led to complete fracture healing.^[105,111] Sonoporation has also been shown effective for in vivo transfection of reporter genes inside

Table 3. Different types of non-viral gene delivery for orthopedic TE.

Types	Advantages	Disadvantages	TE relevant Subtypes	Application for TE in vivo	References
Vector free	Simpler, not viral or chemical carriers needed	Difficult to incorporate to biomaterial-guided approaches Can cause cell and tissue damage	Electroporation Sonoporation	Bone and cartilage Bone, intervertebral disc	[107,108] [105,111,112]
Inorganic vectors	High biocompatibility. Possibility of delivery in serum and serum-free conditions	Low transfection efficiencies	CaP	Bone	[122,124,126,127,206]
Lipid-based vectors	High DNA loading capacity Moderate transfection efficiencies	Cytotoxicity. Low stability Low half-life Interaction with serum	Lipofectamine	Bone, cartilage	[80,154,207–211]
Polymeric vectors	Very diverse (natural and synthetic) Moderate transfection efficiencies Easy to incorporate into biomaterials	Cytotoxicity Immunogenicity	PEI PLGA Chitosan	Muscle, bone, cartilage Cartilage Cartilage and bone	[127,159–164,179,212–216] [217] [191,194]
Protein and peptide vectors	Biodegradability Low toxicity High stability Specificity for delivery Moderate transfection efficiencies	Unexplored for in vivo gene delivery in orthopedic applications			

the rat intervertebral disc and a sustained gene expression up to 24 weeks.^[112]

4.2. Inorganic Vectors

Different inorganic materials including CaPs, gold nanoparticles (Au-NPs), silica, magnesium phosphates, carbon nanotubes (CNTs), and magnetic nanomaterials such as iron oxides have been shown to successfully deliver nucleic acids into cells^[99,113,114] (Figure 4). Inorganic vectors show many advantages such as their ease of production and functionalization, low immunogenicity, high biocompatibility, resistance to microbial attack, and stability^[99,113,114] (Table 3). The most popular vector for bone gene delivery in this category is CaP. Others like Au-NPs, silica, CNTs, and magnetic nanoparticles (MNPs) remain relatively unexplored in TE and regenerative medicine.

CaP have been used extensively for in vitro transfection due to the cationic charge of calcium which allows formation of ionic complexes with the anionic DNA molecule,^[113] protecting the DNA from the degradative action of nucleases.^[115,116] CaP offers many advantages as a gene delivery vector in bone TE, including its biocompatibility, biodegradability,^[117] the predominance of HA in bone composition,^[118] and the efficient delivery in both serum and serum-free conditions.^[119,120] The delivery method is based on the internalization of the complexes through ion channel-mediated endocytosis^[113] and, once inside the cell cytoplasm, on the endosomal escape of the undamaged DNA due to the buffer effect of the CaP on endosomal pH.^[99,121] Due to the increase of the calcium concentration in the cytoplasm upon delivery, the released DNA is able to migrate into the nucleus through the nuclear pore complex thanks to the blocking of IP3.^[113] Incorporation of CaP nanoparticles into different 3D scaffolds has been shown to promote successful

transfection of progenitor cells to enhance their osteogenic differentiation^[75,122–125] and bone formation in vivo in different animal models.^[126,127] Recently, nanohydroxyapatite (nHA)-mediated BMP-2 and VEGF delivery using a collagen scaffold was shown to rapidly accelerate repair in a rat cranial defect in comparison to the same scaffolds loaded with polyethylenimine (PEI) complexed to both genes, suggesting a synergistic effect between nHA and the delivered genes for bone formation.^[127] Similarly, the osteogenic effect of nHA-mediated gene delivery was observed in vitro when delivering the BMP-2 and TGF- β 3 genes to MSCs, increasing mineralization and endochondral ossification.^[75] Incorporation of the BMP-7 and VEGF genes into an injectable nano-CaP paste for bone substitution showed successful MSC transfection as an strategy for the minimally invasive repair of bone defects.^[124] CaP-mediated gene delivery has also been reported to enhance chondrogenic differentiation of stem cells upon gene delivery of TGB- β 1.^[128]

Au-NPs are promising non-viral vectors for TE strategies due to ease of preparation, high surface area, and the possibility of surface functionalization with nucleic acids.^[114,129] Although Au-NPs have been previously used for the delivery of different bioactive molecules in 3D such as BMP-2^[130] as well as microRNA (miRNA) to enhance osteogenic differentiation of MSCs,^[131] their use as gene delivery vectors in orthopedics remains limited. Importantly, the functionalization of Au-NPs with peptides can enhance MSC uptake which is critical as MSCs show a restricted cellular uptake^[132] in comparison to other cell types. Au-NPs have also been used to promote differentiation of stem cells toward the osteogenic lineage.^[133,134]

MNPs, which include the iron oxide nanoparticles, are attractive for drug and gene delivery in orthopedics due to their small sizes and magnetic properties allowing directional targeting when a magnetic field is applied.^[135] MNPs have been shown to successfully delivery nucleic acid cargos in a process known as magnetofection in which a magnetic field is used

for the MNPs-DNA sedimentation onto target cells.^[136] Another approach for this technique is the combination of MNPs with other transfection agents such as viral particles, liposomes, or cationic polymers and combined with nucleic acids to enhance transfection.^[101] As an example of the potential of this approach in regenerative medicine, MNPs were shown to efficiently transfect neural stem cells with reporter and therapeutic genes encoding for fibroblast growth factor 2 (FGF-2).^[137]

4.3. Lipid-Based Vectors

Cationic lipids are positively charged amphiphilic small molecules whose structure allows for the formation of self-assembled vesicles and membranes in an aqueous solution (Figure 4). This is possible due to their structure, divided into three components: 1) a polar head group that interacts with the DNA and the negatively charged cell membrane for internalization, 2) a hydrophobic fatty acid tail that will allow the formation of the lipid bilayer, and 3) a glycerol backbone to link the hydrophilic and hydrophobic domains.^[61,113,138,139] Liposomes are lipid bilayers which can encapsulate hydrophobic compounds such as pDNA, forming a cationic complex which is able to interact with the anionic cell membrane allowing entrance into the cell via endocytosis. Once inside the cell, the destabilization of the endosomal membrane allows the release of the nucleic acid into the cytoplasm for transport into the cell nucleus.^[140] Lipid-based vectors show many advantages such as a versatile structure that can be easily tailored and functionalized for targeted delivery, their wide size range, high DNA loading capacity, and storage stability (Table 3). But due to their cytotoxicity due to membrane destabilization, low stability, low solubility, low half-life, rapid clearance and interaction with serum, their use for orthopedic applications has been limited^[141] (Table 3).

The most commonly used lipid-based vector is the commercially available lipofectamine which has been shown to successfully transfect primary stem cells from diverse origins^[78,89,142–148] with therapeutic genes such as VEGF,^[142,149] TGF- β 1,^[78,143,145,148] mothers against DPP homolog 3 (SMAD3),^[144] BMP-6,^[146] BMP-2,^[78,150] SOX9,^[151] RUNX2,^[89] osterix,^[152] fibromodulin,^[153] and nerve growth factor (NGF)^[90] between others for cartilage, bone, tendon, nerve, and skin repair. Lipofectamine has also been incorporated into different 3D matrices to allow an in situ sustained transfection. The incorporation of liposomes-pDNA complexes into electrospun PCL nanofiber constructs^[89] and porous HA scaffolds^[154] for osteogenic differentiation are good examples of the potential of this approach.

4.4. Polymeric Vectors

Cationic polymeric vectors are, together with lipid-based vectors, one of the most relevant and widely used non-viral gene carriers and they have been considered as the gold standard for non-viral gene transfection.^[155,156] They can interact with anionic DNA and RNA molecules thanks to the cationic groups, mainly amines, present in their structure, forming nanoparticulate complexes

known as polyplexes (Figure 4). Polymeric vectors are chemically diverse and they can be easily functionalized^[61] and show other advantages for orthopedic gene delivery such as their small size, protection against enzymatic degradation, and ease of incorporation into 3D matrices (Table 3). Polymeric vectors can be divided into natural and synthetic polymers depending on their origin. One common limitation of polymeric vectors, especially from synthetic origin, is their cytotoxicity and immunogenicity in vivo.^[157]

One of the most popular synthetic polymeric vectors for gene delivery in regenerative medicine is PEI. This was firstly used by Boussif et al. in 1995,^[158] and it has been shown successful for localized gene transfection in vivo into skeletal muscle,^[159,160] cranial and long bone defects,^[127,161,162] cartilage defects,^[163,164] and arthritis anti-inflammatory treatment.^[165] PEI has been also used in vitro for the transfection of adult somatic and progenitor cells^[166–171] for osteogenic,^[76,161,170,172] tenogenic,^[153] adipogenic,^[173] and chondrogenic^[164,171,174] applications. Although PEI-mediated gene delivery for orthopedic applications has been widely reported in the literature, PEI has been shown to be cytotoxic due to cell membrane and cytoskeletal alterations^[75,175] which have been reported to affect stem cell differentiation.^[75] Additionally, the entrance of the PEI-pDNA complexes into the cell nucleus might lead to PEI-chromosomal DNA interactions which could affect the cell viability and differentiation.^[176–178] Recently, PEI-mediated gene delivery of pDNA encoding for platelet-derived growth factor-BB on a collagen scaffold promoted inflammation and delayed healing when implanted in a rodent periodontal defect model in comparison to the loading of the recombinant protein suggesting that the immunogenicity of PEI could impair tissue repair.^[179] PEI can be modified to increase its transfection efficiency, decrease cytotoxicity,^[180,181] temporally control its delivery,^[160] and facilitate targeting of a specific cell type or population.^[163] For example, covalently modified PEI with a chondrocyte-affinity peptide to specifically target the knee chondrocytes, demonstrated the feasibility of this approach for the treatment of cartilage disorders.^[163]

Other synthetic polymers such as PEG, poly(L-lysine)-palmitic acid, activated polyamidoamine dendrimer, copolymer-protein, and branched triacrylate/amine polycationic polymers (TAPPs), have also been reported to be promising options for gene delivery for bone repair in comparison to PEI and lipid-based vectors.^[182–186] The use of cationic polysaccharides, such as pullulan-spermine, has also been explored for tissue repair in a cartilage defect.^[187]

Natural polymers such as collagen, chitosan, and gelatin are also a promising option for gene delivery in regenerative medicine due to their biocompatibility, cytocompatibility, and ease of incorporation to 3D scaffolds.^[83] Collagen and modified derivatives have been studied for gene delivery. Collagen type I-mediated gene delivery of parathyroid hormone (PTH) in a collagen matrix was shown to promote regeneration in a tibia critical defect in vivo canine model,^[25] while atelocollagen was also found to be promising for the intramuscular administration of therapeutic genes and their sustained delivery.^[188] Chitosan is one of the most relevant natural polymers for non-viral gene delivery due to its biodegradability, biocompatibility, and low cytotoxicity.^[189] The chitosan molecule possesses positively charged amine groups in its backbone that can interact with

the anionic DNA molecule to form positively charged nanoparticulate complexes. Chitosan has been successfully reported to transfect stem cells of human^[190] and animal^[77,146,191,192] origin, to enhance their chondrogenic and osteogenic differentiation, showing less cytotoxicity and comparable transfection efficiencies to lipofectamine and PEI. In vivo, chitosan and its derivatives have been shown to help direct cartilage^[191] and bone^[193,194] regeneration.

4.5. Protein and Peptide Vectors

Protein-based nanocarriers are naturally derived polymers which are biodegradable, have low toxicity, and high stability and binding capacity. Cationic peptides can have basic amino acid residues such as lysine or arginine in their structure which allow to bind nucleic acids forming nanoparticulate complexes^[100,195] (Figure 4). The main advantages of the use of these molecules for nucleic acid delivery, apart from the low cytotoxicity and their stability in serum supplemented conditions, are the possibility to use specific peptide sequences to target the membrane receptors of specific cell types, modulate the release of the nucleic acids to the cell cytoplasm by selectively lysing the endosome, and the use of nuclear localization sequences from viral origin^[100,195–197] (Table 3). There are different bio-inspired peptides available for peptide-guided gene delivery such as the MPG peptide derived from the human immunodeficiency virus (HIV) which facilitates cellular entry, or the nuclear entry sequence of the simian virus 40 (SV40) T antigen which facilitates nuclear delivery.^[198] In order to complex the peptide and the pDNA, the presence of cationic amino acids in their structure such as lysine and arginine is necessary. Synthetic peptides such as the KALA peptide which has multiple lysine residues, and the RALA amphipathic peptide with multiple arginine residues in its structure, are examples of this approach.^[100,199]

Although cell penetrating peptides have shown better transfection efficiencies and less cytotoxicity than Lipofectamine,^[100] PEI,^[100] and viral vectors^[200,201] in vitro, and they have been used to deliver proteins^[202] and Cap^[203] to direct the differentiation of MSCs, their use for gene delivery in orthopedic TE remains relatively unexplored. The peptide transduction domain (PTD) in combination with the GAL4 DNA binding domain was used as gene carrier for the delivery of hypoxia inducible factor 1 alpha (HIF-1 α) gene into human umbilical vein endothelial cells (HUVECs) to enhance angiogenesis in vitro.^[204] The HIF-1 α gene was also delivered by a cysteine-flanked lysine hexamer peptide to promote angiogenesis in vivo.^[205] While the RALA amphipathic peptide has been explored for gene delivery in vitro for osteogenesis and chondrogenic differentiation of MSCs.^[75]

5. Incorporation of Non-Viral Gene Delivery Methods into Materials to Form Gene Activated Scaffolds: pDNA-Vector-Material Interactions

Biomaterials for use as gene activated (GA) scaffolds must not only act to retain the gene of interest in the site of action avoiding uncontrolled diffusion to the surrounding tissues, but also facili-

Figure 5. The incorporation of pDNA into a 3D matrix to form a GA scaffold can be done through physical entrapment, non-covalent interactions, and covalent interaction of the pDNA or pDNA-vector complexes and the selected scaffold biomaterial.^[218]

tate cellular uptake of the desired nucleic acids to secure effective transfection. For this purpose, technologies to maximize DNA presentation, release, and subsequent transfection have been developed. DNA can typically be incorporated with scaffolds by three mechanisms: A) physical entrapment, B) non-covalent interactions, and C) covalent interaction (Figure 5).

5.1. Physical Entrapment

For the physical entrapment method, the pDNA or vector-pDNA complexes are confined within the 3D matrices during the fabrication process (Figure 5) and DNA release depends on the degradation of the matrix.^[218] Different techniques for the entrapment of pDNA and vector-pDNA complexes have been explored but they are limited to the use of high temperatures, organic solvents, and shear stresses during the fabrication process that might result in DNA damage.^[219] Nucleic acid entrapment in porous PLG microspheres through a gas foaming method was shown to sustain temporal pDNA delivery while maintaining the integrity of the DNA molecule during the microsphere fabrication.^[220] PEI-pDNA complexes were also encapsulated in PLG porous scaffolds using the aforementioned method, showing long-term in vivo transfection^[221] and regeneration of a cranial defect model when the BMP-4 gene was delivered.^[215] A different strategy consisting of the in situ cross-linking of PEG networks was shown to entrap pDNA encoding for secreted embryonic alkaline phosphatase (pSEAP) which upon intramuscular injection was able to produce high levels of expression in comparison to repeated DNA injections.^[91] One of the most tunable and explored hydrogel materials for cartilage and bone TE is alginate. The biocompatibility of the gelation method and its pore size, which has been reported to be on the order of 5–6 nm, makes alginate also a good candidate for sustained release of vector-pDNA therapeutics.^[222] Ca-pDNA complexes of around 100nm have been encapsulated

in alginate showing a slow pDNA release profile due to the degradation of the hydrogels.^[122] When pDNA encoding for BMP-2 encapsulated in this alginate system was injected in the back of mice, the gene activated hydrogels were able to form bony tissue in 2 weeks.^[122] Also, physical entrapment of nHA-pDNA complexes in alginate hydrogels and 3D printed bioinks have been shown to allow for sustained gene transfection to encapsulated MSCs over 2 weeks^[125,223] and to promote construct mineralization and vascularization in vivo when BMP-2 and TGF- β 3 genes were co-delivered.^[125] Gene activated alginate hydrogels for the delivery of BMP-2 have also been shown to promote in vivo bone formation in a goat iliac crest model.^[224]

In addition, to modulate the release of entrapped gene therapeutics, the degradation of biomaterials can be tailored to gain temporal control over gene delivery. For example, varying the polymer molecular weight and concentration in alginate hydrogels, Stilhano et al. and Madrigal et al. were able to control the release of encapsulated lentiviral vectors and transfection in vitro and in vivo^[225] and vascularization when VEGF was delivered.^[226]

5.2. Non-Covalent Interactions

Nucleic acid adsorption is based on the non-specific interactions of the pDNA or the pDNA-vector complexes with the material substrate (Figure 5). This method, together with chemical conjugation, allows for the immobilization of the pDNA after the scaffold fabrication process,^[218] avoiding any DNA damage that can result from the material preparation. The nucleic acid release is determined by the molecular interactions between the vector and the scaffold as a result of their molecular composition as well as scaffold degradation. Both free negatively charged DNA and positively charged DNA-vector complexes, can interact with polymeric scaffolds through hydrophobic, electrostatic, and Van der Waals interactions.^[227] Examples of these interactions are the loading of free DNA or DNA complexed to polymeric, lipid-based, and inorganic vectors into 3D porous scaffolds made of natural and synthetic polymeric materials such as collagen, ceramics, ECM, PLG, and PCL between others.^[77,228–230] To promote adsorption, the electrostatic properties of the bulk biomaterial can be tailored. The inclusion of charged moieties or ECM components such as negatively charged sulfated GAGs and heparin binding peptides into collagen porous scaffolds, to promote an optimal electrostatic environment for gene delivery, have been shown to increase the amount of retained cationic PEI-DNA complexes and hence increase transfection.^[231] The modification of collagen scaffolds with poly-L-lysine has also been shown to enhance pDNA retention.^[232] Alternatively, the vector-pDNA complexes can be also modified to improve their affinity with the carrier material. Collagen-mimetic peptides have been linked to DNA polyplexes in order to tune the polyplex retention and release in collagen scaffolds.^[233] Also, increasing the positive charge of the vector has been shown to enhance PEI-pDNA polyplexes adsorption into PLG scaffolds allowing for twofold higher transfection efficiencies than bolus delivery.^[230] Another interesting approach, especially for bone applications, is the adsorption of positively charged vector-pDNA complexes into CaP-based porous scaffolds. The loading of lipofectamine-pDNA complexes

into HA microparticles that were incorporated into high density MSC aggregates allowed for the production of therapeutic levels of bioactive growth factors when BMP-2 and TGF- β 1 were delivered, which enhanced osteogenesis of MSCs in vitro.^[78]

5.3. Covalent Interaction

The adsorption of the nucleic acid material into a 3D material might be limited in TE by the use of conditioned media containing serum proteins and other cellular products that could induce unwanted release of the adsorbed pDNA due to enzymatic reactions or competitive protein adsorption. Chemical immobilization (Figure 5) could overcome these limitations, help reduce the amount of genetic material needed and also allow fine control of the release kinetics. In comparison to non-covalent interactions based on electrostatic or hydrophobic interactions and van der Waals forces, specific interactions can be introduced through complementary functional groups on the vector and the 3D material.^[234] Different immobilization strategies using biotinylation and reactions between the amine or thiol groups present in polymeric materials have been explored to this end. Incorporation of PEI-pDNA complexes by non-specific adsorption, or using covalent biotin/neutravidin conjugation into HyA hydrogels, showed increased transfection and overexpression in the biotinylated complexes.^[227] PEI-pDNA complexes covalently attached to deprotected amino groups in poly(ϵ -CBZ-L-lysine) films have been shown to promote gene delivery in comparison to the adsorbed complexes.^[235] Covalent immobilization of liposome-pDNA complexes into thiol-functionalized PCL nanofiber meshes has also been shown to facilitate the delivery of pDNA encoding RUNX2 to human MSCs and enhanced their osteogenic potential.^[89]

6. Non-Viral Gene Therapy for the Repair of Bone and Cartilage

To date, the application of non-viral GA scaffolds in orthopedics has been primarily limited to the regeneration of bone and cartilage. Although non-viral gene delivery has been explored for the repair of tendon,^[153,236,237] skeletal muscle,^[102–104,159,160,193] meniscus,^[238,239] ligament,^[237] and intervertebral disc,^[112] the use of non-viral biomaterial-guided gene delivery for the repair of these tissues is limited. The following section will focus on the use of non-viral gene therapy for bone and cartilage regeneration.

6.1. Non-Viral Gene Transfer Strategies for Bone Repair

Gene therapy strategies for bone regeneration are based not only in the reconstruction of the cellular and biochemical composition of osseous tissue, but also in the bone development and repair processes. Gene delivery for the treatment of bone fractures and defects has focused on genes encoding for cytokines and transcription factors involved in endochondral and intramembranous ossification for the production of de novo bone tissue, vascularization to facilitate osseointegration and function

Table 4. Non-viral gene delivery approaches for bone regeneration in vivo.

Gene type delivered	Genes	Transfection approach	Method of administration	Model	References
Osteogenic cytokines and transcription factors	BMP-2	In vivo, electrophoresis	Local injection	Rat skeletal muscle injection	[106,240]
	BMP-2	Ex vivo, liposome	Surgical implantation, periosteal explants, GA scaffold	Rat mandible defect	[80]
	BMP-2	In vivo, CaP	Surgical implantation, atelocollagen, GA scaffold	Rat tibia defect	[206]
	BMP-2	In vivo, liposome	Surgical implantation, hydroxyapatite, GA scaffold	Rabbit cranial defect	[154]
	BMP-2	Ex vivo, liposome	Surgical implantation, PEG, scaffold	Porcine cranial defect	[207]
	BMP-2	In vivo, liposome	Local injection	Porcine cranial defect	[208]
	BMP-2	In vivo, entrapment in alginate hydrogels	Surgical implantation, Alginate, GA scaffold	Goat iliac crest	[224]
	BMP-2	In vivo, entrapment in alginate hydrogels	Surgical implantation, alginate, GA scaffold	Subcutaneous, mouse	[241]
	BMP-2	In vivo, CaP	Surgical implantation, alginate, GA scaffold	Subcutaneous mouse	[122]
	BMP-4	In vivo, PEI	Surgical implantation, PLGA, GA scaffold	Rat cranial defect	[215]
	BMP-6	In vivo, sonoporation	Surgical implantation, collagen, GA scaffold	Porcine tibia defect	[105]
	TGF- β 3	In vivo, entrapment in collagen hydrogel	Surgical implantation, collagen, GA scaffold	Rat cranial defect	[242]
	Osterix	Ex vivo, liposome	Local injection	Rabbit, mandibular osteodistraction	[152]
Pro-angiogenic factors	Osterix	Ex vivo, electroporation	Surgical implantation, PLGA, scaffold	Mice, subcutaneous	[108]
	RUNX2	Ex vivo, electroporation	Surgical implantation, PLGA, scaffold	Mice, subcutaneous	[108]
	VEGF	Ex vivo, dendrimer	Surgical implantation, Gelatin, scaffold	Rabbit tibia defect	[243]
	VEGF	In vivo, pDNA adsorption into collagen scaffold	Surgical implantation, collagen, GA scaffold	Rabbit radius defect	[244]
	FGF-2	Ex vivo, liposome	Surgical implantation, β -TCP, scaffold	Rabbit radius defect	[209]
	PDGF	In vivo, PEI	Surgical implantation, collagen, GA scaffold	Periodontal rat defect	[179]
Hormonal factors	PDGF	In vivo, PEI	Surgical implantation, collagen, GA scaffold	Rat cranial defect	[216]
	PTH 1–34	In vivo, pDNA adsorption into collagen scaffold	Surgical implantation, collagen, GA scaffold	Canine femoral defect	[25]

restoration, and hormonal processes to increase tissue quality (Table 4).

6.1.1. Non-Viral Gene Delivery of Osteogenic Cytokines and Transcription Factors for Bone Repair

Two main developmental processes are involved in bone formation: 1) endochondral ossification for long bone formation and 2) intramembranous ossification for the flat bones of the skull, clavicle, and mandible. Endochondral ossification is the process by which bones are derived from a cartilage template due to chondrocyte hypertrophy which leads into mineralization and vascular invasion.^[245] Following these events, osteoblasts begin producing spongy bone and creating a primary ossification center from which bone formation spreads.^[246] Intramembranous ossification starts with MSCs condensation, alkaline phosphatase (ALP)-mediated mineralization of the secreted tissue, and differentiation of the MSCs into osteoblasts to form an ossification center that is subsequently vascularized.^[245]

Non-viral gene delivery of different osteogenic cytokines and transcription factors involved in these developmental processes

has been explored for bone regeneration. Osteogenic factors such as RUNX2 and osterix have been non-virally delivered to stem cells ex vivo to promote osteogenesis and in vivo bone formation^[108,152]. Non-viral gene delivery of cytokines from the TGF- β superfamily such as BMP-2, BMP-4,^[215] BMP-6,^[105] and TGF- β 3^[242] have been extensively investigated for enhanced in vivo bone formation in GA scaffold approaches. Of special importance is BMP-2 which has shown to initiate the cascade of biological events of endochondral ossification^[106,246] and also promote intramembranous ossification.^[106,247] As an example of the potential of BMP-2 to promote bone formation through these two routes, the electroporation of pDNA encoding for BMP-2 into the rat musculoskeletal muscle showed the development of both hypertrophic cartilage regions and intramembranous bone formation.^[106] Different non-viral BMP-2 gene delivery approaches have been explored for the repair of bone defects. Liposome-mediated transfection has been tested for in vivo^[208] and ex vivo^[80,207] gene delivery of BMP2, resulting in the successful repair of critical size bone defects. In terms of GA scaffolds, collagen and HA porous constructs loaded with CaP complexed to pDNA encoding for BMP-2 have been reported to enhance bone repair and bridge rat tibia and cranial defects.^[154,206] Delivery of pDNA encoding for BMP-2 in MSC-laden alginate

hydrogels was also shown to promote ossification and mineralization subcutaneously in vivo^[122,241] and in a goat iliac crest model.^[224]

6.1.2. Non-Viral Gene Delivery of Pro-Angiogenic Factors for Bone Regeneration

Common to both, endochondral and intramembranous ossification, angiogenesis and vascularization are key processes to provide the new bone with enough oxygen and nutrients. VEGF has been identified as one of the most potent promoters of vascularization during endochondral ossification and fracture repair.^[248] Non-viral in vivo and ex vivo delivery of the VEGF gene and posterior implantation in a rabbit bone defects has been shown to promote blood vessel formation, callus maturation, and defect bridging.^[243,244] Another target with which to promote angiogenesis for bone repair is FGF-2.^[249] Non-virally FGF-2 ex vivo transfected BMSCs seeded on tricalcium phosphate (β -TCP) scaffolds increased vascularization of the constructs and bone formation when implanted in bone defects.^[209] Platelet-derived growth factor (PDGF) delivery has also been explored due to its involvement in the stimulation of local angiogenesis and osteoblast migration during bone fracture.^[250] Although collagen-based GA scaffolds containing PEI-pPDGF complexes were shown to enhance bone repair in a rat cranial defect,^[216] in a follow up study using the same system, PDGF overexpression was shown to prolong inflammation and delayed bone healing in vivo.^[179]

6.1.3. Non-Viral Gene Delivery of Hormonal Factors for Bone Regeneration

In order to maintain normal bone growth and homeostasis, hormonal processes are essential for calcium and phosphate absorption, osteoblast activity, matrix production, and bone repair. Different repair strategies have been inspired in these processes. Parathyroid hormone 1–34 (PTH 1–34) has been shown to stimulate osteoblasts to produce new bone matrix resulting in an increase of the bone density, mass, and mechanical strength.^[251] In a phase III clinical trial, PTH 1–34 administration showed a 65% reduction in the risk of vertebral fractures and a 53% reduction in non-vertebral fractures in osteoporotic patients. Due to the promising results in clinical trials, this molecule has been approved by the FDA for the treatment of osteoporosis of men and women. The delivery of the PTH 1–34 gene in a collagen scaffold was shown to promote fracture repair in a canine critical femoral defect.^[25]

6.2. Non-Viral Gene Transfer Strategies for Articular Cartilage Repair

Hyaline cartilage is present in the articulating surfaces of long bones to lubricate movement and provide protection against friction and wear.^[252] Due to its avascular nature and the low mitotic activity of chondrocytes, cartilage shows a low capacity for self-repair upon damage. Gene therapy strategies for cartilage regen-

eration are based not only on the developmental processes of cell differentiation and cartilaginous matrix synthesis, but also on the degradative processes experiment by cartilage during pathological processes such as OA. Gene therapy for the treatment of cartilage and osteochondral defects has traditionally focused on the use of anabolic cytokines and transcription factors and co-factors involved in chondrogenic differentiation and cartilage matrix production, the suppression of chondrocyte hypertrophy and endochondral ossification, and the inhibition of catabolic processes that take place during cartilage pathologies (Table 5).

6.2.1. Chondrogenic Differentiation and Cartilage Matrix Production Strategies

To promote cell differentiation and cartilage matrix production, the anabolic cytokines are a group of genes of major interest for cartilage gene therapy approaches. Overexpression of genes encoding for secreted extracellular growth factors might enhance matrix production in the area defined by the construct, and also on the adjacent tissue facilitating the integration of the newly formed cartilage following in vivo implantation.^[259] Between these, the members of the TGF- β superfamily, TGF- β 1 and 3, are recognized as two of the most important growth factors for cartilage TE,^[260] as they promote chondrocyte proliferation, ECM synthesis,^[261–263] and chondrogenic differentiation of MSCs.^[264–267] For these reasons, gene delivery of TGF- β 1 and 3 has been widely investigated, offering a promising alternative to growth factor supplementation for cartilage TE.^[50,268–271] Regarding non-viral gene delivery of these factors in vivo, pDNA encoding for TGF- β 1 has been complexed to different cationic vectors such as chitosan^[191] and poly(ethylene oxide)-b-poly(L-lysine) (PEO-b-PLL)^[253] and loaded into fibrin-PLGA scaffolds, promoting cartilage repair in a rabbit full-thickness and osteochondral defects. Also, the adsorption of pTGF- β 1 into a chitosan–gelatin scaffold has been shown to promote chondrogenic differentiation of MSCs and hyaline cartilage repair in a rabbit full-thickness cartilage defect.^[254]

Therapeutic targets from the TGF- β superfamily also include the BMPs and the cartilage-derived morphogenic proteins (CDMP). BMP factors play an important role in MSCs and chondrocyte proliferation and differentiation through the crosstalk with the TGF- β isotypes in the SMAD signaling pathway.^[272,273] For these reasons, different BMPs such as BMP-2,^[67] BMP-4,^[274] BMP-6,^[146] and BMP-7^[275] have been investigated in gene delivery approaches to enhance cartilage repair. While the delivery of pDNA encoding for BMP-2 using gene activated fibrin glue offered no significant improvement in rabbit osteochondral defects,^[213] non-viral ex vivo transfection of MSCs with the CDMP gene and posterior seeding in a collagen gel were shown to enhance cartilage repair in vivo.^[257] Apart from the TGF- β proteins, other important anabolic cytokine genes used in GA scaffolds to induce chondrogenesis and cartilage repair in vivo are insulin growth factor 1 (IGF-1) and FGF-2.

The overexpression of transcription factors is another way to induce chondrogenesis and cartilage matrix production. Unlike cytokines, transcription factors are proteins that directly bind to specific DNA sequences promoting or blocking the

Table 5. Non-viral gene delivery approaches for cartilage regeneration in vivo.

Strategy	Genes	Transfection approach	Method of administration	Model	References
Cell differentiation/matrix production	TGF- β 1	In vivo, PLL	Surgical implantation, PLGA, GA scaffold	Rabbit osteochondral defect	[253]
	TGF- β 1	In vivo, chitosan	Surgical implantation, PLGA, GA scaffold	Rabbit full-thickness cartilage defect	[191]
	TGF- β 1	Ex vivo, pullulan-spermine	Surgical implantation, gelatin, scaffold	Rat full-thickness cartilage defect	[187]
	TGF- β 1	In vivo, pDNA adsorption into chitosan–gelatin scaffold	Surgical implantation, chitosan–gelatin, GA scaffold	Rabbit full-thickness cartilage defect	[254]
	IGF-1	Ex vivo, lipoplex	Surgical implantation, alginate, scaffold	Rabbit full-thickness cartilage defect	[255]
	FGF-2	Ex vivo, lipoplex	Surgical implantation, alginate, scaffold	Rabbit osteochondral defect	[256]
	SOX9	Ex vivo, PLGA	Local injection	Mouse subcutaneous	[217]
	CDMP1	Ex vivo, lipoplex	Surgical implantation, collagen gel, scaffold	Rabbit osteochondral defect	[257]
Inhibition of catabolic processes	BMP-2	In vivo, PEI	Surgical implantation, fibrin gel, scaffold	Rabbit osteochondral defect	[213]
	IL-10	In vivo, electrophoresis	Intra-articular injection	Mouse collagen induced arthritis model	[258]
	IL-1RA	In vivo, liposome	Intra-articular injection	Rabbit OA model	[210]

transcription of a gene.^[276] Gene delivery of transcription factors also shows a determinant advantage as these factors cannot be applied as soluble factors and their localization inside the cell confines their effects to only the transfected cells, preventing any undesired accumulation or side-effects in a non-targeted tissue. The most common transcription factors used for gene therapy in cartilage TE are the SOX family, specifically the SOX trio formed by SOX9, SOX5, and SOX6. These have also been identified as key factors for the inhibition of endochondral ossification and chondrocyte hypertrophy, downregulating RUNX2 and cartilage vascularization.^[277,278] As an example, SOX9 transfection of MSCs using PLGA microspheres enhanced the expression of chondrogenic genes and secretion of cartilage-specific matrix after in vivo subcutaneous implantation.^[217]

6.2.2. Inhibition of Endochondral Ossification

To suppress endochondral ossification different genes targeting different processes involved in the conversion of cartilage into bone have been studied. The identification of endochondral ossification and chondrocyte hypertrophy inhibitors is also important for the treatment of OA related pathologies which might result in calcification and vascularization of the damaged cartilage. Between these targets, we can highlight the parathyroid hormone receptor protein (PTHrP), antagonists of BMP like gremlin 1 (GREM1), inhibitors of angiogenesis like chondromodulin 1 (CHM1) and endostatin, and histone deacetylases (HDACs) such as HDAC4 which target the osteogenic gene RUNX2.

PTHrP has been shown to enhance chondrogenic differentiation of MSCs and downregulate the expression of markers of chondrocyte hypertrophy such as collagen type X, RUNX2, and

ALP.^[278] Non-viral co-delivery of TGF- β 1 and PTHrP was hypothesized to promote cartilage matrix production in vitro by chondrocytes and to suppress chondrocyte hypertrophy.^[211]

Antagonists of the BMPs such as GREM1, frizzled related protein, and dickkopf 1 homolog have been identified as one of the most upregulated genes in articular cartilage in comparison to growth plate.^[279] GREM1 has been shown to inhibit chondrocyte hypertrophy and matrix mineralization when supplemented into the culture media in vitro.^[279]

Inhibitors of vascularization such as CHM1 and endostatin are a promising option to inhibit endochondral ossification. Furthermore, vascular invasion into the cartilage surface is a hallmark of OA and numerous angiogenic factors such as VEGF have been detected in the OA affected tissues.^[280,281] Viral-mediated transfection of the CHM1 gene into cartilage lesions in miniature pigs stimulated chondrogenic differentiation of the host progenitor cells and inhibited chondrocyte hypertrophy and vascularization.^[282] In addition, lipoplex-mediated transfection of MSCs in a collagen GA scaffold with the endostatin gene was shown to sustain the expression of the transgene over 14 days in vitro.^[283]

HDAC4 has been shown to modulate cell fate by modifying the chromatin structure and regulating the expression of transcription factors such as RUNX2.^[278] Viral-mediated overexpression of HDAC4 has also shown to support chondrogenesis and suppress the expression of collagen type X.^[284]

6.2.3. Inhibition of Catabolic Processes

As previously defined, OA is the most common joint chronic disorder and a leading cause of disability.^[9,10] The pathology of OA

is very complex and involves the degradation of all the tissues in the joint, being inflammation and catabolic processes the key elements in the development and progression of this disease.^[285]

The group of inflammatory cytokines such as interleukin 1 alpha (IL-1 α), interleukin 1 beta (IL-1 β), and tumor necrosis factor alpha (TNF- α), is the most important group of compounds participating in the pathogenesis of OA, disrupting the metabolic homeostasis of the joint and promoting catabolic and destructive processes.^[286] These inflammatory cytokines have a direct effect over the increased expression of ECM proteases, such as matrix metalloproteases (MMPs) and disintegrin and metalloproteinase with thrombospondin motifs (ADAMTs),^[286,287] which degrade aggrecan and collagen.^[286]

Gene therapy featuring anti-inflammatory cytokines has been shown as an effective way to suppress the inflammatory pathology in OA. Interleukin 1 receptor antagonist (IL-1RA) has been proposed as a promising target to block IL-1 β activation. Retroviral ex vivo gene delivery of IL-1Ra to human arthritic joints has been tested in two clinical trials,^[288,289] while GA scaffolds for lentiviral IL-1Ra gene delivery have been shown to inhibit the negative effects of IL-1 on chondrogenesis of MSCs in vitro.^[66] Also, liposome-based non-viral gene delivery of IL-1RA has been explored, showing suppression of tissue degradation and improved regeneration when delivered through intra-articular injection in a rabbit OA model.^[210] Another anti-inflammatory cytokine explored for this end is interleukin-10 (IL-10), the non-viral delivery of which through intra articular injection has been shown to inhibit the clinical and biological features of arthritis in an arthritic mouse knee.^[258] Viral gene delivery of the tumor necrosis factor antagonist gene (TNFR:Fc) has also been explored as treatment for rheumatoid arthritis.^[49]

The inhibition of catabolic processes has not only focused on the use of anti-inflammatory approaches but also on the direct suppression of tissue degradation by different proteases. Tissue inhibitors of metalloproteinases (TIMPs), which suppress MMP-mediated degradation of the cartilaginous ECM,^[290] are an important target in this approach. The retroviral gene transfer of TIMP-1 into chondrocytes has been shown to inhibit the effects of IL-1 and prevent collagen breakdown in vitro.^[291] Other promising targets are the α 2-macroglobulin (α 2M) protein, which prevents cartilage degradation through inhibition of MMPs,^[292] and the ADAMTs^[293] but their gene transfer remains to be validated for cartilage TE applications.

7. Combinatorial Gene Therapy in Bone and Cartilage Orthopedic Tissue Engineering

Bone and cartilage tissue repair and development are dynamic, highly regulated, and organized processes that are driven by the action of multiple growth factors, for the modulation of different cellular activities such as cell recruitment, mitosis, differentiation, and tissue formation. Moreover, the developmental and pathological processes involving bone and cartilage are complex, and the delivery of just one gene might not be enough to develop a successful regenerative strategy. Combinatorial viral and non-viral gene delivery strategies targeting different processes for bone and cartilage regeneration highlight the importance and feasibility of a multigenic approach to secure a more success-

ful and complete repair that can answer current therapeutic challenges (Table 6).

7.1. Combinatorial Gene Therapy for Bone TE

The first study using non-viral delivery of multiple genes in a GA scaffold for bone regeneration was based on the potential synergistic effects of the co-delivery of PDGF and VEGF for bone regeneration. The combination of the chemotactic and mitogenic effects of PDGF and the angiogenic potential of VEGF were explored by the PEI-mediated delivery of these two genes in vivo using a collagen GA scaffold.^[212] Surprisingly, the co-delivery of both factors reduced bone repair in comparison to the delivery of PDGF gene alone.^[212] The authors hypothesized that a sequential delivery, in order to recapitulate the bone repair processes in which PDGF is secreted first after a fracture and is followed by VEGF expression, could have been beneficial for enhanced bone repair.^[212] Another combinatorial gene delivery approach used in vivo for bone formation is the co-delivery of the BMP-2 and BMP-7 genes whose co-expression have been reported to synergistically enhance osteogenesis of progenitor cells and ALP activity resulting in rapid bone formation,^[296] and ectopic osteogenic differentiation in vivo.^[111] In order to enhance both, bone formation and vascularization, the co-delivery of osteogenic and angiogenic genes such as BMP-2 and VEGF in collagen-based GA scaffold systems have resulted in higher bone formation and vessel formation in rat cranial defects, showing more effective than the delivery of BMP-2 alone.^[127,194] Additionally, co-delivery of TGF- β 3 and BMP-2 in a 3D printed alginate/PCL construct was explored to enhance endochondral ossification of transplanting MSCs, resulting in enhanced GAG, collagen, and calcium deposition in vitro and vascularization and mineralization in vivo.^[125]

7.2. Combinatorial Gene Therapy for Cartilage and OA

For cartilage repair, instead of the promotion of endochondral ossification, the inhibition of this process is desired. One of the problems of the use of factors from the TGF family is the propensity to undergo chondrocyte hypertrophy and endochondral ossification, characterized for deposition of collagen type X, collagen type I, and mineralization of the cartilage templates. For example, in previously mentioned studies, non-viral TGF- β 1 delivery in an osteochondral defect showed collagen type II, aggrecan, and SOX9 expression levels similar to native cartilage but also high levels of collagen type X and I.^[253] In order to suppress this endochondral ossification process, combinatorial gene delivery of inducers of chondrogenesis such as TGF- β 1, BMP-2, and FGF-2, and suppressors of hypertrophy such as PTHrP and SOX9 has been explored to suppress hypertrophic differentiation and enhance stable cartilage repair.^[211,297–299] In addition, the co-delivery of the SOX trio genes has been hypothesized to enhance chondrogenic differentiation and suppress hypertrophy when delivered together in comparison to the administration of these factors individually.^[107,300] PLGA-mediated transfection of a multi-cistronic pDNA encoding for these three genes was also proven superior for chondrogenic differentiation of MSCs than

Table 6. Combinatorial non-viral gene delivery for bone and cartilage regeneration in vivo.

Tissue type	Genes	Transfection approach	Method of administration	Model	References
Bone regeneration	PDG/VEGF	In vivo, PEI	Surgical implantation, collagen, GA scaffold	Rat cranial defect	[212]
	BMP-2/BMP-7	In vivo, sonoporation	Surgical implantation, collagen/fibrin, GA scaffold	Mouse intramuscular	[111]
	BMP-2/BMP-7	In vivo, electroporation	Local injection	Rat intramuscular	[106]
	BMP-2/VEGF	In vivo, nHA/PEI	Surgical implantation, collagen, GA scaffold	Rat cranial defect	[127]
	BMP-2/TGF- β 3	In vivo, nHA	Surgical implantation, 3D printed alginate/PCL composite, GA scaffold	Mouse subcutaneous	[125]
	BMP-2/VEGF	In vivo, chitosan	Surgical implantation, Collagen, GA scaffold	Rat cranial defect	[194]
Cartilage regeneration	IGF-1 /FGF-2	Ex vivo, lipoplex	Surgical implantation, alginate, scaffold	Rabbit osteochondral defect	[294,295]
	TGF- β 1/PTHrP	Ex vivo, liposome	Surgical implantation, PLA, scaffold	Rabbit full-thickness cartilage defect	[211]
	IL-1RA/TGF- β 1	In vivo, liposome	Intra-articular injection	Rabbit OA model	[210]

the transfection of each single gene.^[171] The multi-cistronic approach used by Park et al. for the simultaneous delivery of the SOX trio factors could represent a promising and more efficient alternative to the delivery of multiple individual plasmids, especially for non-viral approaches which show no DNA packing limitations in comparison to viral vectors. IGF-1 and FGF non-viral co-delivery has also been hypothesized to synergistically enhance chondrogenesis and cartilage repair. Induction of chondrogenesis and chondrocyte proliferation due to FGF-2 overexpression and the promotion of cartilage matrix production and phenotype stabilization due to IGF-1 gene delivery have been shown to promote articular cartilage repair and a protective effect in the neighboring cartilage in a rabbit osteochondral defect.^[294,295]

Another promising strategy for the treatment of OA in which both cartilage matrix production and decrease of inflammation are needed, could be the combination of induction of chondrogenesis through the delivery of factors from the TGF- β family and inflammation inhibitors such as IL-10 and IL-1RA. The intra-articular injection of IL-1RA and TGF- β 1 genes complexed to lipofectamine into a rabbit OA model showed better repair outcomes than the injection of the individual genes, and surprisingly offered a synergistic effect as the TGF- β 1 overexpression increased the endogenous expression of IL-1RA.^[210] These results show that GA scaffold-based strategies combining both regenerative and anti-inflammatory gene overexpression could also be successful for the treatment of cartilage defects.

8. Future Directions

8.1. Spatially Defined Gene Delivery

Traditionally, TE strategies have focused on the development of homogenous implants of uniform composition, however in most tissues cells, ECM components and bioactive cues are spatially organized. For example, bone is a complex organ which comprises mineralized osseous tissue, marrow, endosteum, and periosteum nerves and blood vessels which are uniquely organized at different anatomic sites.^[245] Articular cartilage also shows a heteroge-

neous composition formed by a superficial layer of hyaline cartilage, a middle zone, and a deep zone that is calcified at the bone interface^[245] (Figure 6). Successful TE strategies must recapitulate this heterogeneous architecture to produce biologically functional devices that once implanted will perform similarly to native tissues. The engineering of scaffolds with a gradient in composition, structure, mechanical, and chemical properties that can spatially modulate cellular behavior represents an attractive approach for regenerating heterogeneous tissues. This same reasoning can be applied to biomaterial-guided gene delivery, but the spatial presentation of nucleic acids faces many challenges and novel strategies are needed.

For this purpose, biomaterial–nucleic acid interaction is a critical factor, and it must be finely tuned for the effective micropatterning of different genes and gene carriers. While the spatial distribution of nucleic acid adsorbed into 3D porous materials faces multiple challenges, mainly due to diffusion of the loaded genetic material and the unspecific interactions between the DNA and the substrate, DNA entrapment into hydrogels and chemical immobilization might be more suitable approaches for the spatial incorporation of genetic cues. For example, lipoplex-pDNA complexes were chemically immobilized in a polydimethylsiloxane (PDMS) substrate to create 100–1000 μ m wide patterns of transgene expression of NGF for the engineering in vitro of graded neural tissue.^[301] The engineering of pDNA gradients through the production of HA gradients in an electrospun fibrous scaffold, also resulted in zonal reporter gene overexpression,^[302] while entrapment of lipofectamine-pDNA complexes in fibrin hydrogels during the polymerization process was shown to provide confined gene transfer suitable for the development of cell transfection microarrays that could be also used for graded TE.^[303]

Also, different materials loaded with different nucleic acids can be organized following the architecture of the desired tissue in a multilayer approach. The spatial organization of materials with different biological properties could also act synergistically with the delivered genes to promote graded cell differentiation and organized new tissue deposition. A challenge with this approach is preventing the delamination of the multiple layers when implanted in vivo.^[304]

Figure 6. 3D bioprinting of gene activated bioinks for the engineering of spatial complex tissues. A) Structure of articular cartilage and its different mechanical and biochemical properties.^[308,309] B) The incorporation of chondrogenic and osteogenic genes into bioinks to form gene activated bioinks (GABs) could be used for the 3D printing of gene activated constructs to recapitulate cartilage native structure.

8.1.1. Spatial Gene Delivery at the Tissue Interface: The Osteochondral Unit

Since the mechanical and biological functionality of the osteochondral unit depends on the described spatial architecture, it is important that TE strategies reproduce this native structure (Figure 6). Different biomaterials, cell, and protein-based strategies have been explored to this end but challenges remain. For example, the spatial defined deposition of chondrocytes and stem cells in agarose hydrogels promoted zonal chondrogenesis and endochondral ossification in vitro and in vivo.^[305] Also, the spatial differentiation of one progenitor cell type through the zonal presentation of material stiffness and growth factors has also been explored, but limitations to zonally guide stem cell differentiation still persist. For example, the engineering of stem cell-laden constructs composed of a soft chondrogenic layer and a stiffer bone layer was not enough to spatially guide MSC differentiation^[306] and the use of bilayered PLG scaffolds containing a zonal gradient of the growth factors TGF- β 3 and BMP-4, in the cartilage and bone layer respectively, did not result in the formation of stable hyaline cartilage in the top layer.

Similar approaches have been explored for gene delivery to overcome the limitations of spatial growth factor presentation. MSC-laden pTGF- β 1 loaded chitosan–gelatin and pBMP-2 loaded HA/chitosan–gelatin scaffolds were combined through

fibrin glue fixation to create a bilayered osteochondral construct which enabled simultaneous formation of articular cartilage and subchondral bone when implanted in vivo in an osteochondral defect model.^[307] Gene delivery also offers the possibility of the overexpression of transcription factors whose effect is much more localized in comparison to the delivery of growth factors that can diffuse through the construct. Polymeric delivery of pDNA encoding for the SOX trio genes in the cartilage layer, and RUNX2 in the bone layer, was explored to spatially control MSC differentiation in a oligo[poly(ethylene glycol) fumarate] (OPF) hydrogel.^[214] When these constructs were implanted in a rat osteochondral defect, the bilayered scaffolds showed improved healing in comparison to empty controls and the application of only one gene.^[214] The main limitations of this study was the possible interaction between the SOX trio and RUNX2 overexpression which could counteract each other's action and the coupling of the processes of gene transfection and scaffold degradation for the regeneration of higher quality tissue.^[214]

8.1.2. Biofabrication and Gene Delivery

Recently, biofabrication methods have started to gain importance as they allow the production of multiphasic scaffolds that can

Figure 7. Schematic representation of the bioprinting process, with co-deposition of PCL and the gene activated bioink comprising of alginate, nHA-pDNA complexes and MSCs, and the macroscopic appearance of the constructs before implantation. Reproduced with permission.^[125] Copyright 2017, Mary Ann Liebert, Inc.

potentially reproduce the structural and biological cues of intricate tissues.^[310–312] The combination of biofabrication techniques with gene therapy is an interesting option for achieving a zonal distribution of gene encoding for different molecules that can help mimic the zonal genetic gradients found in non-homogenous tissues such as articular cartilage (Figure 6). 3D printing of gene-activated alginate hydrogels has been considered as a promising approach for bone TE,^[313] and thermal inkjet printing has been reported to generate transient pores in the membrane of cells that can be used for pDNA delivery with a 30% transfection efficiency.^[314] Furthermore, the co-printing of gene activated materials and mechanically robust polymers such as PCL can enable the generation of mechanically robust constructs in which multiple layers are mechanically integrated to avoid delamination. Bioprinting might therefore address some of the limitations of traditional TE strategies, including poor layer integration, insufficient mechanical properties, and the scalability of the approach. In addition, more sophisticated patterns of genetic material could be introduced into engineered constructs using bioprinting technology. Recent work from our lab has demonstrated that the incorporation of nHA-mediated gene delivery into alginate-based bioinks allows for the development of novel gene activated bioinks (GABs).^[125] These can then be applied for the engineering of mechanically reinforced constructs through the 3D co-printing of these GABs and PCL, allowing for the fabrication of scalable mechanically robust constructs for bone TE applications^[125] (Figure 7).

8.2. Temporally Controlled Biomaterial-Guided Gene Delivery

The presentation of micro-environmental signals during tissue development and healing is highly regulated, not only spatially but also temporally. Temporal regulation of gene delivery and overexpression has multiple advantages over constitutive gene expression. The overexpression of a specific transgene is usually only required during a determined phase of repair, and its continuous expression could result in impaired cell growth

and differentiation.^[315] For example, for successful cartilage repair, the termination of the overexpression of chondrogenic factors might be required in order to maintain the differentiated state and avoid further differentiation into the hypertrophic or fibroblastic phenotype,^[66] or to avoid undesired abnormal tissue formation and inflammation.^[15] Also, the application of anti-inflammatory gene therapy might impair the inflammatory process required at the early stages of tissue repair.^[316]

In addition, temporal control of gene overexpression is of great importance for combinatorial gene delivery. The presentation of chondrogenic and angiogenic signals at the same time to enhance endochondral ossification might not be ideal as low oxygen levels play an important role in MSC chondrogenesis. Similarly, when trying to engineer multi-layered articular cartilage, the overexpression of inhibitors of chondrocyte hypertrophy in the cartilage layer might also affect the integration with the subchondral bone required in an osteochondral defect model.

Temporal control in non-viral GA scaffold-based gene delivery provides a significant challenge. Recently, the use of ultrasound pulses and pDNA loaded porous constructs has been explored to gain temporal control over the transfection of cells recruited to a bone fracture site.^[105,317] Although this technique allows for on-demand control of gene delivery in the site of injury, it is still unclear how this approach could be applied for the sequential delivery of multiple genes.

Another option to gain temporal control is the use of inducible expression systems such as tetracycline-inducible promoters, also called tetracycline-on (Tet-On). This system is controlled by the administration of tetracycline or doxycycline for induction of transgene expression, meaning that the gene of interest will only be expressed in the presence of a specific drug.^[318] For TE, the Tet-On system has been established for in vivo and in vitro induction of gene expression,^[319] and modulation of the expression of growth factors such as BMP-2^[320] and anti-inflammatory cytokines.^[66] The use of inducible promoters to control the expression of delivered genes might be a promising strategy to temporally recapitulate the processes of tissue formation and healing.

Figure 8. RNA therapeutics for the silencing or activation of molecular targets. A) miRNA delivered to the cell cytoplasm is processed by the endoribonuclease DICER which facilitates the binding of the RNA to RNA-induced silencing complex (RISC) promoting the degradation (antago miR) or activation (Mimic miR) of the complementary mRNA sequence.^[325,338] B) Delivered shRNA or C) dsRNA is processed by DICER resulting in siRNA which binds to RISC and degrades the complementary mRNA strand.^[325,338] D) The delivery of a gene encoding for a target RNAi can also be used to express the desired RNA molecule, resulting in the presence of multiple copies of the RNAi in the cell cytoplasm.^[325,338]

8.3. RNA Delivery as an Alternative for Gene Delivery

The transient silencing of specific genes by RNA technology offers a new therapeutic approach for TERM strategies. This approach offers advantages over DNA delivery since effectiveness of RNA delivery depends only on reaching the cell cytoplasm and not the cell nucleus which is a significant challenge for non-viral vectors^[321,322] (Figure 8). Other advantages of RNA delivery are its specificity and transient effect providing a finer temporal control, RNA extended high life and stability in comparison to pDNA,^[323,324] and it can be easily incorporated into 3D materials for biomaterial-guided RNA delivery.^[325] Different targets and approaches have been investigated for tissue regeneration from which the microRNAs (miRs), short hairpin RNA (shRNA), and short interfering RNA (siRNA) are perhaps the most important (Figure 8). miRs are small non-coding RNAs that can activate (mimic miRNA) or repress (antago miRNA) the translation of specific genes by cleaving messenger RNAs (mRNAs).^[326,327] ShRNA and siRNA are double stranded RNA fragments which induce the catalytic cleavage of complementary strands of mRNA resulting in the silencing of protein production and genetic knockdown.^[328]

Several miRs have been investigated as possible targets for biomaterial-guided cartilage and bone regeneration therapies. In bone TE, most of therapies has focused in miRNA 26a as it

can regulate the endogenous angiogenic–osteogenic coupling for enhanced bone regeneration.^[325,329,330] Also recently, the nHA-mediated delivery of miR-133a-3p in a collagen 3D scaffold increased osteogenesis of MSCs in vitro and in vivo.^[123,325,331] For cartilage regeneration, miR-181b and miR-145 have been identified as suppressors of chondrogenesis and negative regulators of cartilage development, silencing of these miRs by delivery of siRNA for miR-181b and anti-miR-145, respectively, resulted in enhanced chondrogenesis and collagen type II production.^[332,333] A novel promising target for cartilage TE is miR-221 whose silencing has been shown to promote MSC chondrogenesis in vitro without **grow factor** supplementation and to enhance cartilage regeneration in vivo suppressing endochondral ossification.^[334] In addition, the use of RNA delivery for the modulation of immune response and the silencing of inflammatory cytokines has been explored as treatment options for OA.^[335–337]

Another promising strategy involving the use of RNAs for cartilage and bone regeneration is the delivery of protein coding mRNA which serves as a template for cytosolic protein expression without the requirement of nuclear entry, which poses a significant advantage in comparison to DNA delivery and could overcome the lower transfection efficiencies associated with non-viral gene delivery.^[339,340] Moreover, chemical modification and sequence optimization of the mRNA molecule has allowed for enhanced stability and half-life, and reduced

Q11

immunogenicity.^[341–344] Protein coding mRNAs have been explored for enhanced bone formation by the delivery of BMP-2^[345–347] and BMP-9,^[345] tendon regeneration through FGF-2 delivery,^[348] and the treatment of osteoarthritic joints through RUNX delivery.^[349]

9. Toward Translation: From Bench to Bedside

The application of gene therapy in orthopedics has the potential to broaden the field of gene therapy from the treatment of rare genetic diseases toward applicability in the daily life of millions of people suffering from degenerative diseases such as OA. Despite recent progress and optimism in gene therapy application into the clinics, especially after the approval of Invossa for the treatment of OA in South Korea, numerous hurdles still exist for the translation of orthopedic gene therapy strategies from bench to bedside including financial, safety, regulatory, and sociological issues.^[350]

Two significant challenges for the translation of gene therapy toward musculoskeletal clinical applications include the requirement to offer a cost-effective treatment that can provide stable long-term repair of the tissue and its functionality, and the safety of the gene transfer methods. Despite over 1800 clinical trials worldwide,^[30,350] and the approval of seven gene therapies for human use during the 2012–2017 period, gene therapy has been traditionally viewed as an unsafe treatment that will struggle to meet the constraints of the regulatory bodies. This perception might prevent orthopedic gene therapy from being a viable candidate for funding by the large pharmaceutical companies, leaving gene therapy in the hands of start-up companies dependent on venture capital and unable to assume the expense of performing late-stage clinical trials needed for commercialization.^[30,351] In addition to the economic and safety issues, the regulatory constraints that gene therapy must overcome have increased exponentially, resulting in an expensive and time-consuming process. Saying this, while gene therapy faces a difficult translational environment, recent favorable clinical trials and the approval of the first gene therapies for treatment of diverse human diseases have renewed optimism in the field, making the treatment of common musculoskeletal disorders using gene delivery approaches closer to reality than ever before.

10. Conclusion

Direct protein delivery for orthopedic TE is limited by low stability and challenges associated with required controlled and localized release over therapeutically relevant windows. Scaffold-mediated non-viral gene therapy can potentially overcome these limitations and offer a powerful tool for the localized, safe, and effective delivery of therapeutic genes for bone and cartilage regeneration. In this review, the current concepts and strategies for the use of non-viral gene therapy in combination with 3D materials for the repair of bone and cartilage were described. The combination of 3D scaffolds and gene therapeutics depends on a multifactorial design in which the gene delivery vector, the carrier material, and the target tissue must all be carefully considered. Challenges that remain to be addressed include

establishing which transgene combination is optimal for specific aspects of tissue repair, and the engineering of novel systems for the spatiotemporal control of gene delivery to recapitulate the architecture of native tissues and also the signaling cascades of developmental and repair processes. Ultimately, however, we are optimistic that the coming years will see significant advances in materials development (i.e., gene delivery vectors and supportive scaffolds) for effective cartilage and bone repair and the increased likelihood of it being translated clinically for the treatment of traumatic injuries and degenerative diseases such as OA.

Acknowledgements

Funding from Science Foundation Ireland through the Advanced Materials and Bioengineering Research (AMBER) centre and an Investigator Programme grant (12/IA/1554), as well as through the European Research Council (StemRepair, 258463; Joint Print, 647004).

Conflict of Interest

The authors declare no conflict of interest.

Keywords

bone, cartilage, gene-activated scaffolds, non-viral gene delivery, orthopaedic gene therapy, tissue engineering

Received: March 25, 2018

Revised: May 18, 2018

Published online:

- [1] T. Vos, C. Allen, M. Arora, R. M. Barber, Z. A. Bhutta, A. Brown, A. Carter, D. C. Casey, F. J. Charlson, A. Z. Chen, M. Coggeshall, L. Cornaby, L. Dandona, D. J. Dicker, T. Dilegge, H. E. Erskine, A. J. Ferrari, C. Fitzmaurice, T. Fleming, M. H. Forouzanfar, N. Fullman, P. W. Gething, E. M. Goldberg, N. Graetz, J. A. Haagsma, C. O. Johnson, N. J. Kassebaum, T. Kawashima, L. Kemmer, I. A. Khalil, et al., *Lancet* **2016**, 388, 1545.
- [2] L. Calais-Ferreira, V. C. Oliveira, J. M. Craig, L. B. Flander, J. L. Hopfer, L. F. Teixeira-Salmela, P. H. Ferreira, *Brazilian J. Phys. Ther.* **2017**, 22, 184. <https://doi.org/10.1016/j.bjpt.2017.12.004>
- [3] C. J. Murray, T. Vos, R. Lozano, M. Naghavi, A. D. Flaxman, C. Michaud, V. Aboyans, *Lancet* **2012**, 380, 2197.
- [4] E. Yelin, S. Weinstein, T. King, *Semin. Arthritis Rheum.* **2016**, 46, 259.
- [5] C. H. Evans, *Mayo Clin. Proc.*, **2013**, 88, 1323.
- [6] E. Gómez-Barrena, P. Rosset, D. Lozano, J. Stanovici, C. Ermthaller, F. Gerbhard, *Bone* **2015**, 70, 93.
- [7] G. Mathew, B. Hanson, *Indian J. Orthop.* **2009**, 43, 111.
- [8] J. A. Buckwalter, H. J. Mankin, *Instr. Course Lect.* **1998**, 47, 487.
- [9] T. Vos, A. D. Flaxman, M. Naghavi, R. Lozano, C. Michaud, M. Ez-zati, K. Shibuya, J. A. Salomon, S. Abdalla, V. Aboyans, J. Abraham, I. Ackerman, R. Aggarwal, S. Y. Ahn, M. K. Ali, M. Alvarado, H. R. Anderson, L. M. Anderson, K. G. Andrews, C. Atkinson, L. M. Bad-dour, A. N. Bahalim, S. Barker-Collo, L. H. Barrero, D. H. Bartels, M. G. Basáñez, A. Baxter, M. L. Bell, E. J. Benjamin, D. Bennett, et al., *Lancet* **2012**, 380, 2163.
- [10] M. Cross, E. Smith, D. Hoy, S. Nolte, I. Ackerman, M. Fransen, L. Bridgett, S. Williams, F. Guillemin, C. L. Hill, L. L. Laslett, G. Jones,

- F. Cicuttini, R. Osborne, T. Vos, R. Buchbinder, A. Woolf, L. March, *Ann. Rheum. Dis.* **2014**, 73, 1323.
- [11] BCC Research, *Regenerative Medicines: Bone and Joint Applications*, <https://www.bccresearch.com/market-research/pharmaceuticals/regenerative-medicines-bone-joint-applications-phm032d.html>, **2015**.
- [12] J. L. Santos, D. Pandita, J. Rodrigues, A. P. Pêgo, P. L. Granja, H. Tomás, *Curr. Gene Ther.* **2011**, 11, 46.
- [13] M. Heyde, K. A. Partridge, R. O. C. Oreffo, S. M. Howdle, K. M. Shakesheff, M. C. Garnett, *J. Pharm. Pharmacol.* **2007**, 59, 329.
- [14] C. Evans, *Int. Orthop.* **2014**, 38, 1761.
- [15] J. N. Zara, R. K. Siu, X. Zhang, J. Shen, R. Ngo, M. Lee, W. Li, M. Chiang, J. Chung, J. Kwak, B. M. Wu, K. Ting, C. Soo, *Tissue Eng., Part A* **2011**, 17, 1389.
- [16] B. A. Baldo, *Drug Saf.* **2014**, 37, 921.
- [17] E. J. Carragee, E. L. Hurwitz, B. K. Weiner, *Spine J.* **2011**, 11, 471.
- [18] A. R. Poynton, J. M. Lane, *Spine* **2002**, 27, S40.
- [19] C. A. Tannoury, H. S. An, *Spine J.* **2014**, 14, 552.
- [20] T. T. N. Vo, F. K. Kasper, A. G. A. Mikos, *Adv. Drug Deliv. Rev.* **2012**, 64, 1292.
- [21] H. Schliephake, *Oral Maxillofac. Surg.* **2010**, 14, 17.
- [22] S. L. Ginn, I. E. Alexander, M. L. Edelstein, M. R. Abedi, J. Wixon, *J. Gene Med.* **2013**, 15, 65.
- [23] C. H. Evans, J. Huard, *Nat. Rev. Rheumatol.* **2015**, 11, 234.
- [24] N. Ferrer-Miralles, P. Saccardo, J. L. Corchero, Z. Xu, E. García-Fruitós, *Methods Mol. Biol.*, **2015**, 1258, 1.
- [25] J. Bonadio, E. Smiley, P. Patil, S. Goldstein, *Nat. Med.* **1999**, 5, 753.
- [26] R. M. Blaese, K. W. Culver, A. D. Miller, C. S. Carter, T. Fleisher, M. Clerici, G. Shearer, L. Chang, Y. Chiang, P. Tolstoshev, J. J. Greenblatt, S. A. Rosenberg, H. Klein, M. Berger, C. A. Mullen, W. J. Ramsey, L. Muul, R. A. Morgan, W. F. Anderson, *Science* **1995**, 270, 475.
- [27] S. E. Raper, N. Chirmule, F. S. Lee, N. A. Wivel, A. Bagg, G. P. Gao, J. M. Wilson, M. L. Batshaw, *Mol. Genet. Metab.* **2003**, 80, 148.
- [28] S. Hacein-Bey-Abina, C. von Kalle, M. Schmidt, F. Le Deist, N. Wulffraat, E. McIntyre, I. Radford, J.-L. Villeval, C. C. Fraser, M. Cavazzana-Calvo, A. Fischer, *N. Engl. J. Med.* **2003**, 348, 255.
- [29] M. P. McCormack, A. Forster, L. Drynan, R. Pannell, T. H. Rabbitts, *Mol. Cell. Biol.* **2003**, 23, 9003.
- [30] F. D. Ledley, L. M. McNamee, V. Uzdil, I. W. Morgan, *Gene Ther.* **2014**, 21, 188.
- [31] S. Ylä-Herttuala, *Mol. Ther.* **2012**, 20, 1831.
- [32] C. Morrison, *Nat. Biotechnol.* **2015**, 33, 217.
- [33] E. Mulin, 2017 was the year of gene-therapy breakthroughs, <https://www.technologyreview.com/s/609643/2017-was-the-year-of-gene-therapy-breakthroughs/>, (accessed: January 2018).
- [34] A. Regalado, Everything you need to know about gene therapy's most promising year, <https://www.technologyreview.com/s/603206/everything-you-need-to-know-about-gene-therapys-most-promising-year/> (accessed: July 2018).
- [35] L. Galluzzi, P. Martin, *Oncoimmunology* **2017**, 6, <https://doi.org/10.1080/2162402X.2017.1388486>
- [36] V. Golubovskaya, *Cancers* **2017**, 9, 150.
- [37] M. F. Dias, K. Joo, J. A. Kemp, S. L. Fialho, A. da Silva Cunha, S. J. Woo, Y. J. Kwon, *Prog. Retin. Eye Res.* **2017**, 63, 107. <https://doi.org/10.1016/j.preteyeres.2017.10.004>
- [38] J.-A. Ribeil, S. Hacein-Bey-Abina, E. Payen, A. Magnani, M. Semeraro, E. Magrin, L. Caccavelli, B. Neven, P. Bourget, W. El Nemer, P. Bartolucci, L. Weber, H. Puy, J.-F. Meritet, D. Grevent, Y. Beuzard, S. Chrétien, T. Lefebvre, R. W. Ross, O. Negre, G. Veres, L. Sandler, S. Soni, M. de Montalembert, S. Blanche, P. Leboulch, M. Cavazzana, *N. Engl. J. Med.* **2017**, 376, 848.
- [39] Z. Siprashvili, N. T. Nguyen, E. S. Gorell, K. Loutit, P. Khuu, L. K. Furukawa, H. P. Lorenz, T. H. Leung, D. R. Keene, K. E. Rieger, P. Khavari, A. T. Lane, J. Y. Tang, M. P. Marinkovich, *JAMA, J. Am. Med. Assoc.* **2016**, 316, 1808.
- [40] S. Rangarajan, L. Walsh, W. Lester, D. Perry, B. Madan, M. Laffan, H. Yu, C. Vettermann, G. F. Pierce, W. Y. Wong, K. J. Pasi, *N. Engl. J. Med.* **2017**, 377, 5219.bib>
- [41] O. of the Commissioner, n.d.
- [42] C. H. Evans, S. C. Ghivizzani, P. D. Robbins, *J. Am. Acad. Orthop. Surg.* **2018**, 26, e36.
- [43] W.-W. Zhang, L. Li, D. Li, J. Liu, X. Li, W. Li, X. Xu, M. J. Zhang, L. A. Chandler, H. Lin, A. Hu, W. Xu, D. M.-K. Lam, *Hum. Gene Ther.* **2018**, 29, 160.
- [44] S. Ylä-Herttuala, *Mol. Ther.* **2015**, 23, 217.
- [45] P. Newswire, *Amgen News Releases* **2015**.
- [46] N. Touchot, M. Flume, *Genes* **2017**, 8, 78.
- [47] I. Hernandez, V. Prasad, W. F. Gellad, *JAMA Oncol.* **2018**, 4, 994. <https://doi.org/10.1001/jamaoncol.2018.0977>
- [48] Luxturna gene therapy to cost \$425,000 per eye, <https://www.cnn.com/2018/01/03/health/luxturna-price-blindness-drug-bn/index.html> (accessed: July 2018).
- [49] P. J. Mease, N. Wei, E. J. Fudman, A. J. Kivitz, J. Schechtman, R. G. Trapp, K. F. Hobbs, M. Greenwald, A. Hou, S. A. Bookbinder, G. E. Graham, C. W. Wiesenhuber, L. Willis, E. M. Ruderman, J. Z. Forstot, M. J. Maricic, K. H. Dao, C. H. Pritchard, D. N. Fiske, F. X. Burch, H. M. Prupas, P. Anklesaria, A. E. Heald, *J. Rheumatol.* **2010**, 37, 692.
- [50] R. K. Elmallah, J. J. Cherian, J. J. Jauregui, T. P. Pierce, W. B. Beaver, M. a Mont, *Expert Opin. Biol. Ther.* **2015**, 15, 455.
- [51] J. Cho, T. Kim, Y. Park, J. Shin, S. Kang, B. Lee, *Cytotherapy* **2016**, 18, S10.
- [52] R. Dinser, F. Kreppel, F. Zaucke, C. Blank, M. Paulsson, S. Kochanek, P. Maurer, *Histochem. Cell Biol.* **2001**, 116, 69.
- [53] H. Madry, M. Cucchiari, U. Stein, K. Remberger, M. D. Menger, D. Kohn, S. B. Trippel, *J. Gene Med.* **2003**, 5, 502.
- [54] S. Raisin, E. Belamie, M. Morille, *Biomaterials* **2016**, 104, 223.
- [55] H. Madry, M. Cucchiari, *Curr. Rheumatol. Rep.* **2014**, 16, 450.
- [56] J. Fang, Y. Y. Zhu, E. Smiley, J. Bonadio, J. P. Rouleau, S. A. Goldstein, L. K. McCauley, B. L. Davidson, B. J. Roessler, *Proc. Natl. Acad. Sci. U. S. A.* **1996**, 93, 5753.
- [57] I. Y. Bozo, R. V. Deev, A. Y. Drobyshev, A. A. Isaev, I. I. Eremin, *Case Rep. Dent.* **2016**, 2016, 1.
- [58] R. Masgutov, M. Chekunov, M. Zhuravleva, G. Masgutova, O. Teplov, R. Salikhov, D. Galimov, Y. Plakseichuk, A. Rizvanov, *Bio-nanoscience* **2017**, 7, 194.
- [59] W. Wang, W. Li, N. Ma, G. Steinhoff, *Curr. Pharm. Biotechnol.* **2013**, 14, 46.
- [60] A. Saraf, A. G. Mikos, *Adv. Drug Deliv. Rev.* **2006**, 58, 592.
- [61] H. Yin, R. L. Kanasty, A. A. Eltoukhy, A. J. Vegas, J. R. Dorkin, D. G. Anderson, *Nat. Rev. Genet.* **2014**, 15, 541.
- [62] D. A. Williams, A. J. Thrasher, *Stem Cells Transl. Med.* **2014**, 3, 636.
- [63] P. Ueblicher, B. Wagner, S. Vogt, G. Salzmann, G. Wexel, A. Krüger, C. Plank, T. Brill, K. Specht, T. Hennig, U. Schillinger, A. B. Imhoff, V. Martinek, B. Gansbacher, *Biomaterials* **2007**, 28, 4480.
- [64] J. M. Brunger, N. P. T. Huynh, C. M. Guenther, P. Perez-Pinera, F. T. Moutos, J. Sanchez-Adams, C. A. Gersbach, F. Guilak, *Proc. Natl. Acad. Sci. U. S. A.* **2014**, 111, E798.
- [65] L. Cao, F. Yang, G. Liu, D. Yu, H. Li, Q. Fan, Y. Gan, T. Tang, K. Dai, *Biomaterials* **2011**, 32, 3910.
- [66] K. A. Glass, J. M. Link, J. M. Brunger, F. T. Moutos, C. A. Gersbach, F. Guilak, *Biomaterials* **2014**, 35, 5921.
- [67] K. Gelse, C. Mühle, O. Franke, J. Park, M. Jehle, K. Durst, M. Göken, F. Hennig, K. von der Mark, H. Schneider, *Arthritis Rheum.* **2008**, 58, 475.
- [68] A. Pascher, G. Palmer, A. Steinert, T. Oligino, E. Gouze, J.-N. Gouze, O. Betz, M. Spector, P. Robbins, C. Evans, S. Ghivizzani, *Gene Ther.* **2004**, 11, 133.

- [69] B. T. Feeley, A. H. Conduah, O. Sugiyama, L. Krennek, I. S. Y. Chen, J. R. Lieberman, *J. Orthop. Res.* **2006**, *24*, 1709.
- [70] J. K. Venkatesan, M. Ekici, H. Madry, G. Schmitt, D. Kohn, M. Cucchiari, *Stem Cell Res. Ther.* **2012**, *3*, 22.
- [71] J. Frisch, P. Orth, A. Rey-Rico, J. K. Venkatesan, G. Schmitt, H. Madry, D. Kohn, M. Cucchiari, *J. Cell. Mol. Med.* **2017**, *21*, 2748.
- [72] A. Rey-Rico, H. Babicz, H. Madry, A. Concheiro, C. Alvarez-Lorenzo, M. Cucchiari, *Int. J. Pharm.* **2017**, *531*, 492.
- [73] K. Rapti, F. Stillitano, I. Karakikes, M. Nonnenmacher, T. Weber, J. S. Hulot, R. J. Hajjar, *Mol. Ther.–Methods Clin. Dev.* **2015**, *2*, <https://doi.org/10.1038/mtm.2014.67>
- [74] N. Halim, K. Fakiruddin, S. Ali, B. Yahaya, *Int. J. Mol. Sci.* **2014**, *15*, 15044.
- [75] T. Gonzalez-Fernandez, B. N. N. Sathy, C. Hobbs, G. M. M. Cuniffe, H. O. O. McCarthy, N. J. J. Dunne, V. Nicolosi, F. J. J. O'Brien, D. J. Kelly, *Acta Biomater.* **2017**, *55*, 226.
- [76] J. Yue, J. Wu, D. Liu, X. Zhao, W. W. Lu, *Nanoscale Res. Lett.* **2015**, *10*, 203. <https://doi.org/10.1186/s11671-015-0906-3>
- [77] R. M. Raftery, E. G. Tierney, C. M. Curtin, S. A. Cryan, F. J. O'Brien, *J. Control. Release* **2015**, *210*, 84.
- [78] A. McMillan, M. K. Nguyen, T. Gonzalez-Fernandez, P. Ge, X. Yu, W. L. Murphy, D. J. Kelly, E. Alsberg, *Biomaterials* **2018**, *161*, 240.
- [79] Z. Mi, S. C. Ghivizzani, E. Lechman, J. C. Glorioso, C. H. Evans, P. D. Robbins, *Arthritis Res. Ther.* **2003**, *5*, R132.
- [80] J. Park, J. Ries, K. Gelse, F. Kloss, K. von der Mark, J. Wiltfang, F. W. Neukam, H. Schneider, *Gene Ther.* **2003**, *10*, 1089.
- [81] S.-D. Li, L. Huang, *J. Control. Release* **2007**, *123*, 181.
- [82] S. J. Lee, J. J. Yoo, A. Atala, *Clinical Regenerative Medicine in Urology*, Springer, Singapore **2018**, 17–51.
- [83] J. M. Dang, K. W. Leong, *Adv. Drug Deliv. Rev.* **2006**, *58*, 487.
- [84] F. Everaerts, M. Torrianni, M. Hendriks, J. Feijen, *J. Biomed. Mater. Res., Part A* **2008**, *85*, 547.
- [85] A. K. B. Bedran-Russo, P. N. R. Pereira, W. R. Duarte, J. L. Drummond, M. Yamaychi, *J. Biomed. Mater. Res., Part B Appl. Biomater.* **2007**, *80*, 268.
- [86] S. Browne, G. Fontana, B. J. Rodriguez, A. Pandit, *Mol. Pharm.* **2012**, *9*, 3099.
- [87] F. J. O'Brien, B. A. Harley, I. V. Yannas, L. J. Gibson, *Biomaterials* **2005**, *26*, 433.
- [88] R. M. Capito, M. Spector, *Gene Ther.* **2007**, *14*, 721.
- [89] N. Monteiro, D. Ribeiro, A. Martins, S. Faria, N. A. Fonseca, J. N. Moreira, R. L. Reis, N. M. Neves, *ACS Nano* **2014**, *8*, 8082.
- [90] K. J. Whittlesey, L. D. Shea, *Biomaterials* **2006**, *27*, 2477.
- [91] K. Roy, D. Wang, M. L. Hedley, S. P. Barman, *Mol. Ther.* **2003**, *7*, 401.
- [92] O. Jeon, M. Krebs, E. Alsberg, *J. Biomed. Mater. Res. A* **2011**, *98*, 72.
- [93] P. D. Benya, J. D. Shaffer, *Cell* **1982**, *30*, 215.
- [94] S. Heiligenstein, M. Cucchiari, M. W. Laschke, R. M. Bohle, D. Kohn, M. D. Menger, H. Madry, *Tissue Eng., Part C. Methods* **2011**, *17*, 829.
- [95] A. Goren, N. Dahan, E. Goren, L. Baruch, M. Machluf, *FASEB J.* **2010**, *24*, 22.
- [96] H. J. Häuselmann, K. Masuda, E. B. Hunziker, M. Neidhart, S. S. Mok, B. A. Michel, E. J. Thonar, *Am. J. Physiol.* **1996**, *271*, 742.
- [97] D. S. W. Benoit, M. P. Schwartz, A. R. Durney, K. S. Anseth, *Nat. Mater.* **2008**, *7*, 816.
- [98] J. M. Meacham, K. Durvasula, F. L. Degertekin, A. G. Fedorov, *J. Lab. Autom.* **2014**, *19*, 1.
- [99] D. E. Wagner, S. B. Bhaduri, *Tissue Eng., Part B Rev.* **2012**, *18*, 1.
- [100] H. O. McCarthy, J. McCaffrey, C. M. McCrudden, A. Zholobenko, A. Ali, J. W. McBride, A. S. Massey, S. Pentlavalli, K.-H. Chen, G. Cole, S. P. Loughran, N. J. Dunne, R. F. Donnelly, V. L. Kett, T. Robson, *J. Control. Release* **2014**, *189C*, 141.
- [101] A. J. Mellott, M. L. Forrest, M. S. Detamore, *Ann. Biomed. Eng.* **2013**, *41*, 446.
- [102] A. V. Zelenin, V. A. Kolesnikov, O. A. Tarasenko, R. A. Shafei, I. A. Zelenina, V. V. Mikhailov, M. L. Semenova, D. V. Kovalenko, O. V. Artemyeva, T. E. Ivaschenko, O. V. Evgrafov, G. Dickson, V. S. Baranovand, *FEBS Lett.* **1997**, *414*, 319.
- [103] L. M. Mir, M. F. Bureau, J. Gehl, R. Rangara, D. Rouy, J. M. Caillaud, P. Delaere, D. Branellec, B. Schwartz, D. Scherman, *Proc. Natl. Acad. Sci. U. S. A.* **1999**, *96*, 4262.
- [104] M. DiFranco, M. Quinonez, J. Capote, J. Vergara, *J. Vis. Exp.* **2009**, <https://doi.org/10.3797/1520>
- [105] M. Bez, D. Sheyn, W. Tawackoli, P. Avalos, G. Shapiro, J. C. Giaconi, X. Da, S. Ben David, J. Gavrity, H. A. Awad, H. W. Bae, E. J. Ley, T. J. Kremen, Z. Gazit, K. W. Ferrara, G. Pelled, D. Gazit, *Sci. Transl. Med.* **2017**, *9*, <https://doi.org/10.1126/scitranslmed.aal3128>
- [106] M. Kawai, K. Bessho, H. Maruyama, J.-I. Miyazaki, T. Yamamoto, *Anat. Rec. Part A Discov. Mol. Cell. Evol. Biol.* **2005**, *287A*, 1264.
- [107] G.-I. Im, H.-J. Kim, *Osteoarthr. Cartil.* **2011**, *19*, 449.
- [108] J.-S. Lee, J.-M. Lee, G.-I. Im, *Biomaterials* **2011**, *32*, 760.
- [109] Q.-W. Wang, Z.-L. Chen, Y.-J. Piao, *J. Biosci. Bioeng.* **2005**, *100*, 418.
- [110] A. Rizk, B. M. Rabie, *Biores. Open Access* **2013**, *2*, 155.
- [111] N. Nomikou, G. A. A. Feichtinger, S. Saha, S. Nuernberger, P. Heilmel, H. Redl, A. P. P. Mchale, *J. Tissue Eng. Regen. Med.* **2017**, <https://doi.org/10.1002/term.2406>
- [112] K. Nishida, M. Doita, T. Takada, K. Kakutani, H. Miyamoto, T. Shimomura, K. Maeno, M. Kurosaka, *Spine* **2006**, *31*, 1415.
- [113] S. Dizaj, S. Jafari, A. Khosroushahi, *Nanoscale Res. Lett.* **2014**, *9*, 252.
- [114] M. K. Riley, W. Vermerris, W. Vermerris, *Nanomaterials* **2017**, *7*, 94. <https://doi.org/10.3390/nano7050094>
- [115] M. Brundin, D. Figdor, G. Sundqvist, U. Sjögren, *J. Endod.* **2013**, *39*, 211.
- [116] G. Zuo, Y. Wan, X. Meng, Q. Zhao, K. Ren, S. Jia, J. Wang, *Mater. Chem. Phys.* **2011**, *126*, 470.
- [117] W. Habraken, P. Habibovic, M. Epple, M. Böhner, *Mater. Today* **2016**, *19*, 69.
- [118] A. L. Boskey, *Bonekey Rep.* **2013**, *2*, 447.
- [119] H. Fu, Y. Hu, T. McNelis, J. O. Hollinger, *J. Biomed. Mater. Res., Part A* **2005**, *74A*, 40.
- [120] C. M. Curtin, G. M. Cuniffe, F. G. Lyons, K. Bessho, G. R. Dickson, G. P. Duffy, F. J. O'Brien, *Adv. Mater.* **2012**, *24*, 749.
- [121] I. Nabiev, S. Mitchell, A. Davies, Y. Williams, D. Kelleher, R. Moore, Y. K. Gun'ko, S. Byrne, Y. P. Rakovich, J. F. Donegan, A. Sukhanova, J. Conroy, D. Cottell, N. Gaponik, A. Rogach, Y. Volkov, *Nano Lett.* **2007**, *7*, 3452.
- [122] M. D. Krebs, E. Salter, E. Chen, K. A. Sutter, E. Alsberg, *J. Biomed. Mater. Res. A* **2010**, *92*, 1131.
- [123] I. M. Castaño, C. M. Curtin, G. Shaw, J. Mary Murphy, G. P. Duffy, F. J. O'Brien, *J. Control. Release* **2014**, *200*, 42.
- [124] S. Chernousova, J. Klesing, N. Soklakova, M. Epple, *RSC Adv.* **2013**, *3*, 11155.
- [125] G. M. Cuniffe, T. Gonzalez-Fernandez, A. Daly, B. N. Sathy, O. Jeon, E. Alsberg, D. J. Kelly, *Tissue Eng., Part A* **2017**, *23*, 891.
- [126] M. Keeney, J. J. P. van den Beucken, P. M. van der Kraan, J. A. Jansen, A. Pandit, *Biomaterials* **2010**, *31*, 2893.
- [127] C. M. Curtin, E. G. Tierney, K. McSorley, S.-A. Cryan, G. P. Duffy, F. J. O'Brien, *Adv. Healthc. Mater.* **2015**, *4*, 223.
- [128] X. Cao, W. Deng, Y. Wei, Y. Yang, W. Su, Y. Wei, X. Xu, J. Yu, *Eur. Cell. Mater.* **2012**, *23*, 81.
- [129] S. Vial, R. L. Reis, J. M. Oliveira, *Curr. Opin. Solid State Mater. Sci.* **2017**, *21*, 92.
- [130] C. J. Kearney, H. Skaat, S. M. Kennedy, J. Hu, M. Darnell, T. M. Raimondo, D. J. Mooney, *Adv. Healthc. Mater.* **2015**, *4*, 1634.
- [131] M. Yu, B. Lei, C. Gao, J. Yan, P. X. Ma, *Nano Res.* **2017**, *10*, 49.
- [132] L.-H. Peng, J. Niu, C.-Z. Zhang, W. Yu, J.-H. Wu, Y.-H. Shan, X.-R. Wang, Y.-Q. Shen, Z.-W. Mao, W.-Q. Liang, J.-Q. Gao, *Biomaterials* **2014**, *35*, 5605.

- [133] C. Yi, D. Liu, C.-C. Fong, J. Zhang, M. Yang, *ACS Nano* **2010**, *4*, 6439.
- [134] D. N. Heo, W.-K. Ko, M. S. Bae, J. B. Lee, D.-W. Lee, W. Byun, C. H. Lee, E.-C. Kim, B.-Y. Jung, I. K. Kwon, E. H. Hwang, I. K. Kwon, *J. Mater. Chem. B* **2014**, *2*, 1584.
- [135] Y. Gao, J. Lim, S.-H. Teoh, C. Xu, *Chem. Soc. Rev.* **2015**, *44*, 6306.
- [136] C. Plank, O. Zelphati, O. Mykhaylyk, *Adv. Drug Deliv. Rev.* **2011**, *63*, 1300.
- [137] M. Pickard, C. Adams, P. Barraud, D. Chari, *J. Funct. Biomater.* **2015**, *6*, 259.
- [138] N. Monteiro, A. Martins, R. L. Reis, N. M. Neves, *J. R. Soc. Interface* **2014**, *11*.
- [139] A. D. Bangham, M. M. Standish, J. C. Watkins, *J. Mol. Biol.* **1965**, *13*, 238.
- [140] Y. Xu, F. C. Szoka, *Biochemistry* **1996**, *35*, 5616.
- [141] H. Lv, S. Zhang, B. Wang, S. Cui, J. Yan, *J. Control. Release* **2006**, *114*, 100.
- [142] P. Locatelli, F. D. Olea, A. Hnatiuk, D. Sepúlveda, J. M. Pérez Sáez, R. Argüello, A. Crottogini, *Cytotherapy* **2013**, *15*, 163.
- [143] C.-A. Guo, X.-G. Liu, J.-Z. Huo, C. Jiang, X.-J. Wen, Z.-R. Chen, *J. Biosci. Bioeng.* **2007**, *103*, 547.
- [144] Q. Zheng, Y. Wang, X. Gu, *J. Huazhong Univ. Sci. Technol. Med. Sci.* **2005**, *25*, 674.
- [145] X. Guo, J. Du, Q. Zheng, S. Yang, Y. Liu, D. Duan, C. Yi, *J. Huazhong Univ. Sci. Technol. Med. Sci.* **2002**, *22*, 112.
- [146] G. K. Kayabaşı, R. S. T. Aydin, M. Gümüşderelioğlu, *J. Biomed. Mater. Res. A* **2013**, *101*, 1353.
- [147] S. Elser, S. Schetting, G. Schmitt, D. Kohn, H. Madry, M. Cucchiari, *J. Gene Med.* **2012**, *14*, 501.
- [148] B. Li, F. Li, L. Ma, J. Yang, C. Wang, D. Wang, C. Gao, *Mol. Pharm.* **2014**, *11*, 2062.
- [149] W. Michlits, R. Mittermayr, R. Schäfer, H. Redl, S. Aharinejad, *Wound Repair Regen.* **2007**, *15*, 360.
- [150] F. Wegman, A. Bijenhof, L. Schuijff, F. C. Oner, W. J. Dhert, J. Alblas, *Eur. Cell. Mater.* **2011**, *21*, 230.
- [151] Y. Yao, Y. He, Q. Guan, Q. Wu, *Biomaterials* **2014**, *35*, 1898.
- [152] Q.-G. Lai, K.-F. Yuan, X. Xu, D. Li, G.-J. Li, F.-L. Wei, Z.-J. Yang, S.-L. Luo, X.-P. Tang, S. Li, *Oral Surg. Oral Med. Oral Pathol. Oral Radiol. Endod.* **2011**, *111*, 412.
- [153] A. Delalande, M. P. Gosselin, A. Suwalski, W. Guilmain, C. Leduc, M. Berchel, P. A. Jaffrès, P. Baril, P. Midoux, C. Pichon, *Nanomedicine* **2015**, *11*, 1735.
- [154] I. Ono, T. Yamashita, H.-Y. Jin, Y. Ito, H. Hamada, Y. Akasaka, M. Nakasu, T. Ogawa, K. Jimbow, *Biomaterials* **2004**, *25*, 4709.
- [155] J. A. Fortune, B. A. Chemistry, *J. M. Essigmann*, **2010**.
- [156] S. Patnaik, K. C. Gupta, *Expert Opin. Drug Deliv.* **2013**, *10*, 215.
- [157] X. Zhao, X. Li, Y. Zhao, Y. Cheng, Y. Yang, Z. Fang, Y. Xie, Y. Liu, Y. Chen, Y. Ouyang, W. Yuan, *Front. Pharmacol.* **2017**, *8*, 510.
- [158] O. Boussif, F. Lezoualc'h, M. A. Zanta, M. D. Mergny, D. Scherman, B. Demeneix, J. P. Behr, *Proc. Natl. Acad. Sci. U. S. A.* **1995**, *92*, 7297.
- [159] J. W. Hong, J. H. Park, K. M. Huh, H. Chung, I. C. Kwon, S. Y. Jeong, *J. Control. Release* **2004**, *99*, 167.
- [160] M. Türk, S. Dincer, E. Pişkin, *J. Tissue Eng. Regen. Med.* **2007**, *1*, 377.
- [161] H. Cheong, K.-H. Kim, Y.-J. Park, T.-I. Kim, Y.-M. Lee, Y. Ku, I.-C. Rhyu, D.-S. Lee, S.-J. Lee, C.-P. Chung, S.-B. Han, Y.-J. Seol, *J. Korean Acad. Periodontol.* **2007**, *37*, 859.
- [162] C. Qiao, K. Zhang, H. Jin, L. Miao, C. Shi, X. Liu, A. Yuan, J. Liu, D. Li, C. Zheng, G. Zhang, X. Li, B. Yang, H. Sun, *Int. J. Nanomedicine* **2013**, *8*, 2985.
- [163] Y. Pi, X. Zhang, J. Shi, J. Zhu, W. Chen, C. Zhang, W. Gao, C. Zhou, Y. Ao, *Biomaterials* **2011**, *32*, 6324.
- [164] G.-I. Im, H.-J. Kim, J. H. Lee, *Biomaterials* **2011**, *32*, 4385.
- [165] S. Xiang, J. Su, H. Tong, F. Yang, W. Tong, W. Yuan, F. Wu, C. Wang, T. Jin, K. Dai, X. Zhang, *Biomaterials* **2012**, *33*, 6520.
- [166] W. Wang, W. Li, L. Ou, E. Flick, P. Mark, C. Nesselmann, C. A. Lux, H. H. Gatzert, A. Kaminski, A. Liebold, K. Lützow, A. Lendlein, R. K. Li, G. Steinhoff, N. Ma, *J. Cell. Mol. Med.* **2011**, *15*, 1989.
- [167] J. S. Park, K. Na, D. G. Woo, H. N. Yang, J. M. Kim, J. H. Kim, H.-M. Chung, K.-H. Park, *Biomaterials* **2010**, *31*, 124.
- [168] H. H. Ahn, J. H. Y. Lee, K. S. Kim, J. H. Y. Lee, M. S. Kim, G. Khang, I. W. Lee, H. B. Lee, *Biomaterials* **2008**, *29*, 2415.
- [169] B. I. Florea, C. Meaney, H. E. Junginger, G. Borchard, *AAPS Pharm-SciTech* **2002**, *4*, E12.
- [170] Q. F. Wang, Y. Huang, G. C. He, H. S. Wang, Z. H. Chen, X. H. Cai, Y. H. Xie, Q. Liu, *Genet. Mol. Res.* **2017**, *16*, <https://doi.org/10.4238/gmr16015358>
- [171] J. S. Park, S. W. Yi, H. J. Kim, S. M. Kim, J.-H. Kim, K.-H. Park, *ACS Appl. Mater. Interfaces* **2017**, *9*, 1361.
- [172] E. G. Tierney, K. McSorley, C. L. Hastings, S.-A. Cryan, T. O'Brien, M. J. Murphy, F. P. Barry, F. J. O'Brien, G. P. Duffy, *J. Control. Release* **2013**, *165*, 173.
- [173] D. Joydeep, Y.-J. Choi, H. Yasuda, J. W. Han, C. Park, H. Song, H. Bae, J.-H. Kim, *Sci. Rep.* **2016**, *6*, 33784.
- [174] J. S. Park, H. N. Yang, D. G. Woo, S. Y. Jeon, K.-H. Park, *Biomaterials* **2012**, *33*, 7151.
- [175] S. M. Moghimi, P. Symonds, J. C. Murray, A. C. Hunter, G. Debska, A. Szewczyk, *Mol. Ther.* **2005**, *11*, 990.
- [176] W. T. Godbey, K. K. Wu, A. G. Mikos, *Biomaterials* **2001**, *22*, 471.
- [177] S. Akhtar, *Gene Ther.* **2006**, *13*, 739.
- [178] A. K. Larsen, A. C. Hunter, L. Parhamifar, S. M. Moghimi, T. L. Andresen, *Soft Matter* **2010**, *6*, 4001.
- [179] A. B. Plonka, B. Khorsand, N. Yu, J. V. Sugai, A. K. Salem, W. V. Giannobile, S. Elangovan, *Gene Ther.* **2017**, *24*, 31.
- [180] M. Thomas, J. J. Lu, C. Zhang, J. Chen, A. M. Klibanov, *Pharm. Res.* **2007**, *24*, 1564.
- [181] M. Thomas, A. M. Klibanov, *Proc. Natl. Acad. Sci. U. S. A.* **2002**, *99*, 14640.
- [182] K. Itaka, S. Ohba, K. Miyata, H. Kawaguchi, K. Nakamura, T. Takato, U.-I. Chung, K. Kataoka, *Mol. Ther.* **2007**, *15*, 1655.
- [183] B. A. Clements, V. Incani, C. Kucharski, A. Lavanifan, B. Ritchie, H. Uludağ, *Biomaterials* **2007**, *28*, 4693.
- [184] S. A. Chew, J. D. Kretlow, P. P. Spicer, A. W. Edwards, L. S. Baggett, Y. Tabata, F. K. Kasper, A. G. Mikos, *Tissue Eng., Part A* **2011**, *17*, 751.
- [185] D. P. Walsh, A. Heise, F. J. O'Brien, S.-A. Cryan, *Gene Ther.* **2017**, *24*, 681.
- [186] P. Schwabe, S. Greiner, R. Ganzert, J. Eberhart, K. Dähn, A. Stemberger, C. Plank, G. Schmidmaier, B. Wildemann, *Sci. World J.* **2012**, *2012*, 1.
- [187] C.-X. He, T.-Y. Zhang, P.-H. Miao, Z.-J. Hu, M. Han, Y. Tabata, Y.-L. Hu, J.-Q. Gao, *Biotechnol. Appl. Biochem.* **2012**, *59*, 163.
- [188] A. Sano, *Adv. Drug Deliv. Rev.* **2003**, *55*, 1651.
- [189] R. Raftery, F. J. O'Brien, S.-A. Cryan, *Molecules* **2013**, *18*, 5611.
- [190] K. Corsi, F. Chellat, L. Yahia, J. C. Fernandes, *Biomaterials* **2003**, *24*, 1255.
- [191] W. Wang, B. Li, Y. Li, Y. Jiang, H. Ouyang, C. Gao, *Biomaterials* **2010**, *31*, 5953.
- [192] X. Xu, S. Qiu, Y. Zhang, J. Yin, S. Min, *Artif. Cells, Nanomed., Biotechnol.* **2017**, *45*, 330.
- [193] S. Mansouri, P. Lavigne, K. Corsi, M. Benderdour, E. Beaumont, J. C. Fernandes, *Eur. J. Pharm. Biopharm.* **2004**, *57*, 1.
- [194] R. M. Raftery, I. Mencía Castaño, G. Chen, B. Cavanagh, B. Quinn, C. M. Curtin, S. A. Cryan, F. J. O'Brien, *Biomaterials* **2017**, *149*, 116.
- [195] M. E. Martin, K. G. Rice, *AAPS J.* **2007**, *9*, E18.
- [196] B. Gupta, T. S. Levchenko, V. P. Torchilin, *Adv. Drug Deliv. Rev.* **2005**, *57*, 637.
- [197] E. A. Nigg, *Nature* **1997**, *386*, 779.
- [198] M. Morris, P. Vidal, L. Chaloin, F. Heitz, G. Divita, *Nucleic Acids Res.* **1997**, *25*, 2730.

- [199] T. B. Wyman, F. Nicol, O. Zelphati, P. V. Scaria, C. Plank, F. C. Szoka, *Biochemistry* **1997**, *36*, 3008.
- [200] A. Ho, S. R. Schwarze, S. J. Mermelstein, G. Waksman, S. F. Dowdy, *Cancer Res.* **2001**, *61*, 474.
- [201] J. S. Wadia, S. F. Dowdy, *Curr. Opin. Biotechnol.* **2002**, *13*, 52.
- [202] J. Jo, S. Hong, W. Y. Choi, D. R. Lee, *Sci. Rep.* **2014**, *4*, 4378.
- [203] B. N. Sathy, D. Olvera, T. Gonzalez-Fernandez, G. Inne, M. Cuniffe, S. Pentlavalli, P. Chambers, O. Jeon, E. Alsberg, H. O. McCarthy, N. Dunne, T. L. Haut, D. Gh, D. J. Kelly, *J. Mater. Chem. B* **2017**, *5*, 1753.
- [204] M. Jeon, Y. Shin, J. Jung, U.-W. Jung, J.-H. Lee, J. S. Jeon, I. Kim, J.-S. Shin, S.-K. Lee, J. S. Song, *Mol. Cell. Biochem.* **2017**, *1*.
- [205] D. Trentin, H. Hall, S. Wechsler, J. A. Hubbell, *Proc. Natl. Acad. Sci. U. S. A.* **2006**, *103*, 2506.
- [206] M. Endo, S. Kuroda, H. Kondo, Y. Maruoka, K. Ohya, S. Kasugai, *Tissue Eng.* **2006**, *12*, 489.
- [207] F. Wehrhan, K. Amann, A. Molenberg, R. Lutz, F. W. Neukam, K. A. Schlegel, *Clin. Oral Implants Res.* **2012**, *23*, 805.
- [208] J. Park, R. Lutz, E. Felszeghy, J. Wiltfang, E. Nkenke, F. W. Neukam, K. A. Schlegel, *Biomaterials* **2007**, *28*, 2772.
- [209] X. Guo, Q. Zheng, I. Kulbatski, Q. Yuan, S. Yang, Z. Shao, H. Wang, B. Xiao, Z. Pan, S. Tang, *Biomed. Mater.* **2006**, *1*, 93.
- [210] P. Zhang, Z.-H. Zhong, H.-T. Yu, B. Liu, *Scand. J. Rheumatol.* **2015**, *44*, 404.
- [211] R. S. Goomer, L. J. Deftos, R. Terkeltaub, T. Maris, M. C. Lee, F. L. Harwood, D. Amiel, *Osteoarthr. Cartil.* **2001**, *9*, 248.
- [212] S. R. D'Mello, S. Elangovan, L. Hong, R. D. Ross, D. R. Sumner, A. K. Salem, *Curr. Pharm. Biotechnol.* **2015**, *16*, 655.
- [213] U. Schillinger, G. Wexel, C. Hacker, M. Kullmer, C. Koch, M. Gerg, S. Vogt, P. Ueblicher, T. Tischer, D. Hensler, J. Wilisch, J. Aigner, A. Walch, A. Stemberger, C. Plank, *Pharm. Res.* **2008**, *25*, 2946.
- [214] C. J. Needham, S. R. Shah, R. L. Dahlin, L. A. Kinard, J. Lam, B. M. Watson, S. Lu, F. K. Kasper, A. G. Mikos, *Acta Biomater.* **2014**, *10*, 4103.
- [215] Y.-C. Huang, C. Simmons, D. Kaigler, K. G. Rice, D. J. Mooney, *Gene Ther.* **2005**, *12*, 418.
- [216] S. Elangovan, S. R. D'Mello, L. Hong, R. D. Ross, C. Allamargot, D. V. Dawson, C. M. Stanford, G. K. Johnson, D. R. Sumner, A. K. Salem, *Biomaterials* **2014**, *35*, 737.
- [217] S. Y. Jeon, J. S. Park, H. N. Yang, D. G. Woo, K.-H. Park, *Biomaterials* **2012**, *33*, 4413.
- [218] L. De Laporte, L. D. Shea, *Adv. Drug Deliv. Rev.* **2007**, *59*, 292.
- [219] J.-H. Jang, L. D. Shea, *J. Control. Release* **2003**, *86*, 157.
- [220] D. J. Mooney, L. D. Shea, E. Smiley, J. Bonadio, *Nat. Biotechnol.* **1999**, *17*, 551.
- [221] Y.-C. Huang, K. Riddle, K. G. Rice, D. J. Mooney, *Hum. Gene Ther.* **2005**, *16*, 609.
- [222] T. Boonthekul, H.-J. J. Kong, D. J. Mooney, *Biomaterials* **2005**, *26*, 2455.
- [223] T. Gonzalez-Fernandez, E. G. E. G. Tierney, G. M. G. M. Cuniffe, F. J. F. J. O'Brien, D. J. D. J. Kelly, *Tissue Eng., Part A* **2016**, *22*, 776.
- [224] L. D. Loozen, Y. J. M. van der Helm, F. C. Öner, W. J. Dhert, M. C. Kruij, J. Alblas, *Tissue Eng., Part A* **2015**, *21*, 1672.
- [225] R. S. Stilhano, J. L. Madrigal, K. Wong, P. A. Williams, P. K. M. Martin, F. S. M. Yamaguchi, V. Y. Samoto, S. W. Han, E. A. Silva, *J. Control. Release* **2016**, *237*, 42.
- [226] J. L. Madrigal, S. N. Sharma, K. T. Campbell, R. S. Stilhano, R. Gijssbers, E. A. Silva, *Acta Biomater.* **2018**, *69*, 265.
- [227] T. Segura, P. H. Chung, L. D. Shea, *Biomaterials* **2005**, *26*, 1575.
- [228] L. Peng, X. Cheng, R. Zhuo, J. Lan, Y. Wang, B. Shi, S. Li, *J. Biomed. Mater. Res., Part A* **2009**, *90A*, 564.
- [229] E. G. Tierney, G. P. Duffy, A. J. Hibbitts, S.-A. Cryan, F. J. O'Brien, *J. Control. Release* **2012**, *158*, 304.
- [230] J.-H. Jang, Z. Bengali, T. L. Houchin, L. D. Shea, *J. Biomed. Mater. Res. A* **2006**, *77*, 50.
- [231] R. A. Hortensius, J. R. Becraft, D. W. Pack, B. A. C. Harley, *Biomater. Sci.* **2015**, *3*, 645.
- [232] H. Cohen-Sacks, V. Elazar, J. Gao, A. Golomb, H. Adwan, N. Korchoy, R. J. Levy, M. R. Berger, G. Golomb, *J. Control. Release* **2004**, *95*, 309.
- [233] M. A. Urello, K. L. Kiick, M. O. Sullivan, *J. Mater. Chem. B* **2014**, *2*, 8174.
- [234] A. K. Pannier, L. D. Shea, *Mol. Ther.* **2004**, *10*, 19.
- [235] J. Zheng, W. S. Manuel, P. J. Hornsby, *Biotechnol. Prog.* **2000**, *16*, 254.
- [236] R. S. Goomer, T. M. Maris, R. Gelber, J. A. M. Boyer, M. Silva, D. Amiel, *Clin. Orthop. Relat. Res.* **2000**, *S189*.
- [237] T. G. Gerich, S. Ghivizani, F. H. Fu, P. D. Robbins, C. H. Evans, *Wien. Klin. Wochenschr.* **1997**, *109*, 384.
- [238] H. Zhang, P. Leng, J. Zhang, *Clin. Orthop. Relat. Res.* **2009**, *467*, 3165.
- [239] H.-P. Lee, A. Rey-Rico, M. Cucchiari, H. Madry, *Int. Orthop.* **2014**, *38*, 1931.
- [240] M. Kawai, K. Bessho, S. Kaihara, J. Sonobe, K. Oda, T. Iizuka, H. Maruyama, *Hum. Gene Ther.* **2003**, *14*, 1547.
- [241] F. Wegman, Y. van der Helm, F. C. Öner, W. J. Dhert, J. Alblas, *Tissue Eng., Part A* **2013**, *19*, 2686.
- [242] S. Premaraj, B. Mundy, J. Parker-Barnes, P. Winnard, A. Moursi, *Orthod. Craniofac. Res.* **2005**, *8*, 320.
- [243] R. Li, D. J. Stewart, H. P. von Schroeder, E. S. Mackinnon, E. H. Schemitsch, *J. Orthop. Res.* **2009**, *27*, 8.
- [244] F. Geiger, H. Bertram, I. Berger, H. Lorenz, O. Wall, C. Eckhardt, H.-G. Simank, W. Richter, *J. Bone Miner. Res.* **2005**, *20*, 2028.
- [245] F. Martini, J. Nath, E. Bartholomew, *Fundamentals of Anatomy and Physiology*, **2009**.
- [246] Y. Y. Yu, S. Lieu, C. Lu, C. Colnot, *Bone* **2010**, *47*, 65.
- [247] T. Stoeger, G. E. Proetzel, H. Welzel, A. Papadimitriou, C. Dony, R. Balling, C. Hofmann, *Growth Factors* **2002**, *20*, 197.
- [248] J. Street, M. Bao, L. deGuzman, S. Bunting, F. V. Peale, N. Ferrara, H. Steinmetz, J. Hoeffel, J. L. Cleland, A. Daugherty, N. van Bruggen, H. P. Redmond, R. A. D. Carano, E. H. Filvaroff, E. H. Filvaroff, *Proc. Natl. Acad. Sci. U. S. A.* **2002**, *99*, 9656.
- [249] M. L. Radomsky, A. Y. Thompson, R. C. Spiro, J. W. Poser, *Clin. Orthop. Relat. Res.* **1998**, *S283*.
- [250] A. I. Caplan, D. Correa, *J. Orthop. Res.* **2011**, *29*, 1795.
- [251] J. L. Vahle, M. Sato, G. G. Long, J. K. Young, P. C. Francis, J. A. Engelhardt, M. S. Westmore, Y. L. Ma, J. B. Nold, *Toxicol. Pathol.* **2002**, *30*, 312.
- [252] G. A. Ateshian, V. C. Mow, *Frict. Lubr. wear Articul. Cartil. diarthrodial joints* **2005**, *447*.
- [253] B. Li, J. Yang, L. Ma, F. Li, Z. Tu, C. Gao, *J. Biomed. Mater. Res., Part A* **2013**, *101*, 3097.
- [254] H. Diao, J. Wang, C. Shen, S. Xia, T. Guo, L. Dong, C. Zhang, J. Chen, J. Zhao, J. Zhang, *Tissue Eng., Part A* **2009**, *15*, 2687.
- [255] H. Madry, G. Kaul, M. Cucchiari, U. Stein, D. Zurakowski, K. Remberger, M. D. Menger, D. Kohn, S. B. Trippel, *Gene Ther.* **2005**, *12*, 1171.
- [256] G. Kaul, M. Cucchiari, D. Arntzen, D. Zurakowski, M. D. Menger, D. Kohn, S. B. Trippel, H. Madry, *J. Gene Med.* **2006**, *8*, 100.
- [257] R. Katayama, S. Wakitani, N. Tsumaki, Y. Morita, I. Matsushita, R. Gejo, T. Kimura, *Rheumatology* **2004**, *43*, 980.
- [258] M. Khoury, P. Bigey, P. Louis-Pence, D. Noel, H. Rhin, D. Scherman, C. Jorgensen, F. Apparailly, *J. Gene Med.* **2006**, *8*, 1027.
- [259] H. Madry, G. Kaul, D. Zurakowski, G. Vunjak-Novakovic, M. Cucchiari, *Eur. Cells Mater.* **2012**, *25*, 229.
- [260] L. Kock, C. C. van Donkelaar, K. Ito, *Cell Tissue Res.* **2012**, *347*, 613.
- [261] T. I. Morales, *Arch. Biochem. Biophys.* **1991**, *286*, 99.
- [262] P. van der Kraan, E. Vitters, W. van den Berg, *J. Rheumatol.* **1992**, *19*, 140.
- [263] J. A. Roman-Blas, D. G. Stokes, S. A. Jimenez, *Osteoarthritis Cartilage* **2007**, *15*, 1367.

- [264] B. Johnstone, T. M. Hering, A. I. Caplan, V. M. Goldberg, J. U. Yoo, *Exp. Cell Res.* **1998**, *238*, 265.
- [265] R. M. Schulz, M. Zscharnack, I. Hanisch, M. Geiling, P. Hepp, A. Bader, *Biomed. Mater. Eng.* **2008**, *18*, S55.
- [266] H. V Almeida, Y. Liu, G. M. Cuniffe, K. J. Mulhall, A. Matsiko, C. T. Buckley, F. J. O'Brien, D. J. Kelly, *Acta Biomater.* **2014**, *10*, 4400.
- [267] A. M. Mackay, S. C. Beck, J. M. Murphy, F. P. Barry, C. O. Chichester, M. F. Pittenger, *Tissue Eng.* **1998**, *4*, 415.
- [268] M. R. Pagnotto, Z. Wang, J. C. Karpie, M. Ferretti, X. Xiao, C. R. Chu, *Gene Ther.* **2007**, *14*, 804.
- [269] A. Ivkovic, A. Pascher, D. Hudetz, D. Maticic, M. Jelic, S. Dickinson, M. Loparic, M. Haspl, R. Windhager, M. Pecina, *Gene Ther.* **2010**, *17*, 779.
- [270] J. Hao, Y. Yao, R. R. Varshney, L. Wang, C. Prakash, H. Li, D.-A. Wang, *Tissue Eng., Part C. Methods* **2008**, *14*, 273.
- [271] F. Zhang, K. Su, Y. Fang, S. Sandhya, D.-A. Wang, *J. Tissue Eng. Regen. Med.* **2015**, *9*, 77.
- [272] B. Keller, T. Yang, Y. Chen, E. Munivez, T. Bertin, B. Zabel, B. Lee, *PLoS One* **2011**, *6*, e16421.
- [273] B. S. Yoon, D. A. Ovchinnikov, I. Yoshii, Y. Mishina, R. R. Behringer, K. M. Lyons, *Proc. Natl. Acad. Sci. U. S. A.* **2005**, *102*, 5062.
- [274] J. Shi, X. Zhang, J. Zhu, Y. Pi, X. Hu, C. Zhou, Y. Ao, *Arthroscopy* **2013**, *29*, 2001.
- [275] D. A. Grande, J. Mason, E. Light, D. Dines, *J. Bone Joint Surg. Am.* **2003**, *85*, 111.
- [276] D. S. Latchman, *Int. J. Biochem. Cell Biol.* **1997**, *29*, 1305.
- [277] T. Hattori, C. Müller, S. Gebhard, E. Bauer, F. Pausch, B. Schlund, M. R. Bösl, A. Hess, C. Surmann-Schmitt, H. von der Mark, B. de Crombrughe, K. von der Mark, *Development* **2010**, *137*, 901.
- [278] S. Chen, P. Fu, R. Cong, H. S. Wu, M. Pei, *Genes Dis.* **2015**, *2*, 76.
- [279] J. C. H. Leijten, J. Emons, C. Sticht, S. van Gool, E. Decker, A. Uiterlinden, G. Rappold, A. Hofman, F. Rivadeneira, S. Scherjon, J. M. Wit, J. van Meurs, C. A. van Blitterswijk, M. Karperien, *Arthritis Rheum.* **2012**, *64*, 3302.
- [280] S. Suri, D. A. Walsh, *Bone* **2012**, *51*, 204.
- [281] B. Deng, C. Chen, X. Gong, L. Guo, H. Chen, L. Yin, L. Yang, F. Wang, *Mol. Med. Rep.* **2017**, *16*, 2142.
- [282] P. Klinger, C. Surmann-Schmitt, M. Brem, B. Swoboda, J. H. Distler, H. D. Carl, K. Von Der Mark, F. F. Hennig, K. Gelse, *Arthritis Rheum.* **2011**, *63*, 2721.
- [283] X. D. Sun, L. Jeng, C. Bolliet, B. R. Olsen, M. Spector, *Biomaterials* **2009**, *30*, 1222.
- [284] M. Pei, D. Chen, J. Li, L. Wei, *Differentiation* **2009**, *78*, 260.
- [285] M. B. Goldring, M. Otero, *Curr. Opin. Rheumatol.* **2011**, *23*, 471.
- [286] P. Wojdasiewicz, Ł. A. Poniatowski, D. Szukiewicz, *Mediators Inflamm.* **2014**, *2014*, 561459.
- [287] M. B. Goldring, *Curr. Rheumatol. Rep.* **2000**, *2*, 459.
- [288] C. H. Evans, P. D. Robbins, S. C. Ghivizzani, M. C. Wasko, M. M. Tomaino, R. Kang, T. A. Muzzonigro, M. Vogt, E. M. Elder, T. L. Whiteside, S. C. Watkins, J. H. Herndon, *Proc. Natl. Acad. Sci. U. S. A.* **2005**, *102*, 8698.
- [289] P. Wehling, J. Reinecke, A. W. A. Baltzer, M. Granrath, K. P. Schulitz, C. Schultz, R. Krauspe, T. W. Whiteside, E. Elder, S. C. Ghivizzani, P. D. Robbins, C. H. Evans, *Hum. Gene Ther.* **2009**, *20*, 97.
- [290] K. Brew, D. Dinakarpanian, H. Nagase, *Biochim. Biophys. Acta* **2000**, *1477*, 267.
- [291] W. Kafienah, F. Al-Fayez, A. P. Hollander, M. D. Barker, *Arthritis Rheum.* **2003**, *48*, 709.
- [292] I. Tchetverikov, N. Verzijl, T. W. Huizenga, J. M. TeKoppele, R. Hane-maaijer, J. DeGroot, *Clin. Exp. Rheumatol.* **2011**, *29*, 711.
- [293] M. D. Tortorella, E. C. Arner, R. Hills, A. Easton, J. Korte-Sarfaty, K. Fok, A. J. Wittwer, R.-Q. Liu, A.-M. Malfait, *J. Biol. Chem.* **2004**, *279*, 17554.
- [294] H. Madry, P. Orth, G. Kaul, D. Zurakowski, M. D. Menger, D. Kohn, M. Cucchiari, *Arch. Orthop. Trauma Surg.* **2010**, *130*, 1311.
- [295] P. Orth, G. Kaul, M. Cucchiari, D. Zurakowski, M. D. Menger, D. Kohn, H. Madry, *Knee Surgery, Sport. Traumatol. Arthrosc.* **2011**, *19*, 2119.
- [296] C. De Bari, F. Dell'Accio, J. Vanlauwe, J. Eyckmans, I. M. Khan, C. W. Archer, E. A. Jones, D. McGonagle, T. A. Mitsiadis, C. Pitzalis, F. P. Luyten, J. Park, T. He, *Arthritis Rheum.* **2006**, *54*, 1209.
- [297] B.-H. Cha, J.-H. Kim, S.-W. Kang, H.-J. Do, J.-W. Jang, Y. R. Choi, H. Park, B.-S. Kim, S.-H. Lee, *Cell Transplant* **2013**, *22*, 1519.
- [298] J. Liao, N. Hu, N. Zhou, L. Lin, C. Zhao, S. Yi, T. Fan, W. Bao, X. Liang, H. Chen, W. Xu, C. Chen, Q. Cheng, Y. Zeng, W. Si, Z. Yang, W. Huang, *PLoS One* **2014**, *9*, e89025.
- [299] M. Cucchiari, E. F. Terwilliger, D. Kohn, H. Madry, *J. Cell. Mol. Med.* **2009**, *13*, 2476.
- [300] V. Lefebvre, P. Li, B. de Crombrughe, *EMBO J.* **1998**, *17*, 5718.
- [301] T. Houchin-Ray, K. J. Whittlesey, L. D. Shea, *Mol. Ther.* **2007**, *15*, 705.
- [302] B. Zou, Y. Liu, X. Luo, F. Chen, X. Guo, X. Li, *Acta Biomater.* **2012**, *8*, 1576.
- [303] P. Lei, R. M. Padmashali, S. T. Andreadis, *Biomaterials* **2009**, *30*, 3790.
- [304] P. Nooeaid, V. Salih, J. P. Beier, A. R. Boccaccini, *J. Cell. Mol. Med.* **2012**, *16*, 2247.
- [305] E. J. Sheehy, T. Vinardell, C. T. Buckley, D. J. Kelly, *Acta Biomater.* **2013**, *9*, 5484.
- [306] N. J. Steinmetz, E. A. Aisenbrey, K. K. Westbrook, H. J. Qi, S. J. Bryant, *Acta Biomater.* **2015**, *21*, 142.
- [307] J. Chen, H. Chen, P. Li, H. Diao, S. Zhu, L. Dong, R. Wang, T. Guo, J. Zhao, J. Zhang, *Biomaterials* **2011**, *32*, 4793.
- [308] T. J. Klein, J. Malda, R. L. Sah, D. W. Huttmacher, *Tissue Eng., Part B. Rev.* **2009**, *15*, 143.
- [309] L. H. Nguyen, A. K. Kudva, N. S. Saxena, K. Roy, *Biomaterials* **2011**, *32*, 6946.
- [310] S. Lopa, H. Madry, *Tissue Eng., Part A* **2014**, *20*, 2052.
- [311] K. Shimomura, Y. Moriguchi, C. D. Murawski, H. Yoshikawa, N. Nakamura, *Tissue Eng., Part B. Rev.* **2014**, *20*, 468.
- [312] J. Visser, F. P. W. Melchels, J. E. Jeon, E. M. van Bussel, L. S. Kimpton, H. M. Byrne, W. J. A. Dhert, P. D. Dalton, D. W. Huttmacher, J. Malda, *Nat. Commun.* **2015**, *6*, 6933.
- [313] L. D. Loozen, F. Wegman, F. C. Öner, W. J. Dhert, J. Alblas, *J. Mater. Chem. B* **2013**, *1*, 6619.
- [314] X. Cui, D. Dean, Z. M. Ruggeri, T. Boland, *Biotechnol. Bioeng.* **2010**, *106*, 963.
- [315] R. G. Crystal, *Science* **1995**, *270*, 404.
- [316] L. C. Gerstenfeld, D. M. Cullinane, G. L. Barnes, D. T. Graves, T. A. Einhorn, *J. Cell. Biochem.* **2003**, *88*, 873.
- [317] G. Shapiro, I. Kallai, D. Sheyn, W. Tawackoli, Y. Do Koh, H. Bae, T. Trietel, R. Goldbart, J. Kost, Z. Gazit, D. Gazit, G. Pelled, *Polym. Adv. Technol.* **2014**, *25*, 525.
- [318] M. Gossen, H. Bujard, *Proc. Natl. Acad. Sci. U. S. A.* **1992**, *89*, 5547.
- [319] P. Ueblicher, B. Wagner, A. Krüger, S. Vogt, G. DeSantis, E. Kennerknecht, T. Brill, M. Hillemanns, G. M. Salzmann, A. B. Imhoff, C. Plank, B. Gänbacher, V. Martinek, *Osteoarthritis Cartilage* **2004**, *12*, 711.
- [320] D. Wübbenhorst, K. Dumler, B. Wagner, G. Wexel, A. Imhoff, B. Gansbacher, S. Vogt, M. Anton, *Arthritis Rheum.* **2010**, *62*, 2037.
- [321] C. Sheridan, *Nat. Biotechnol.* **2011**, *29*, 121.
- [322] A. Yamamoto, M. Kormann, J. Rosenecker, C. Rudolph, *Eur. J. Pharm. Biopharm.* **2009**, *71*, 484.
- [323] E. E. Vaughan, J. V. DeGiulio, D. A. Dean, *Curr. Gene Ther.* **2006**, *6*, 671.
- [324] M. J. Marzi, F. Ghini, B. Cerruti, S. De Pretis, P. Bonetti, C. Giacomelli, M. M. Gorski, T. Kress, M. Pelizzola, H. Muller, B. Amati, F. Nicassio, *Genome Res.* **2016**, *26*, 554.

- [325] C. M. Curtin, I. M. Castaño, F. J. O'Brien, *Adv. Healthc. Mater.* **2018**, *7*, <https://doi.org/10.1002/adhm.201700695>
- [326] A. McAlinden, N. Varghese, L. Wirthlin, L. Chang, *PLoS One* **2013**, *8*, e75012.
- [327] E. Hong, A. H. Reddi, *Tissue Eng., Part B. Rev.* **2012**, *18*, 445.
- [328] G. J. Hannon, *Nature* **2002**, *418*, 244.
- [329] Z. Wang, D. Zhang, Z. Hu, J. Cheng, C. Zhuo, X. Fang, Y. Xing, *Mol. Med. Rep.* **2015**, *12*, 3345.
- [330] J. Malmö, H. Sörgård, K. M. Vårum, S. P. Strand, *J. Control. Release* **2012**, *158*, 261.
- [331] I. Menciá Castañó, C. M. Curtin, G. P. Duffy, F. J. O'Brien, *Sci. Rep.* **2016**, *6*, <https://doi.org/10.1038/srep27941>
- [332] J. Song, M. Lee, D. Kim, J. Han, C.-H. Chun, E.-J. Jin, *Biochem. Biophys. Res. Commun.* **2013**, *431*, 210.
- [333] B. Yang, H. Guo, Y. Zhang, L. Chen, D. Ying, S. Dong, *PLoS One* **2011**, *6*, e21679.
- [334] A. Lolli, R. Narcisi, E. Lambertini, L. Penolazzi, M. Angelozzi, N. Kops, S. Gasparini, G. J. V. M. van Osch, R. Piva, *Stem Cells* **2016**, *34*, 1801.
- [335] A. J. Nixon, L. R. Goodrich, M. S. Scimeca, T. H. Witte, L. V Schnabel, A. E. Watts, P. D. Robbins, *Ann. N. Y. Acad. Sci.* **2007**, *1117*, 310.
- [336] M. Khoury, V. Escriviou, G. Courties, A. Galy, R. Yao, C. Largeau, D. Scherman, C. Jorgensen, F. Apparailly, *Arthritis Rheum.* **2008**, *58*, 2356.
- [337] L. X. Chen, L. Lin, H. J. Wang, X. L. Wei, X. Fu, J. Y. Zhang, C. L. Yu, *Osteoarthritis Cartilage* **2008**, *16*, 174.
- [338] E. Check, *Nature* **2007**, *448*, 855.
- [339] S. Zou, K. Scarfo, M. H. Nantz, J. G. Hecker, *Int. J. Pharm.* **2010**, *389*, 232.
- [340] S. Patel, A. Athirasala, P. de Sousa Menezes, N. Ashwanikumar, T. Zou, G. Sahay, L. B. Boni, *Tissue Eng., Part A* **2018**, <https://doi.org/10.1089/ten.TEA.2017.0444>
- [341] H. Youn, J.-K. Chung, *Expert Opin. Biol. Ther.* **2015**, *15*, 1337.
- [342] S. Uchida, K. Kataoka, K. Itaka, *Pharmaceutics* **2015**, *7*, 137.
- [343] M. Ferizi, M. K. Aneja, E. R. Balmayor, Z. S. Badiyean, O. Mykhaylyk, C. Rudolph, C. Plank, *Sci. Rep.* **2016**, *6*, 39149.
- [344] Z. Trepotec, M. Aneja, J. Geiger, G. Hasenpusch, C. Plank, C. Rudolph, *Tissue Eng., Part A* **2018**, <https://doi.org/10.1089/ten.TEA.2017.0485>
- [345] B. Khorsand, S. Elangovan, L. Hong, A. Dewerth, M. S. D. Kormann, A. K. Salem, *AAPS J.* **2017**, *19*, 438.
- [346] E. R. Balmayor, J. P. Geiger, M. K. Aneja, T. Berezanskyy, M. Utzinger, O. Mykhaylyk, C. Rudolph, C. Plank, *Biomaterials* **2016**, *87*, 131.
- [347] E. R. Balmayor, J. P. Geiger, C. Koch, M. K. Aneja, M. van Griensven, C. Rudolph, C. Plank, *Stem Cells Dev.* **2017**, *26*, 25.
- [348] E. Herbst, F. Imhoff, P. Foehr, S. Milz, C. Plank, C. Rudolph, G. Hasenpusch, J. Geiger, M. Aneja, K. Groth, S. Vogt, A. Imhoff, A. Schmitt, *Tissue Eng., Part A* **2018**, <https://doi.org/10.1089/ten.TEA.2017.0443>
- [349] H. Aini, K. Itaka, A. Fujisawa, H. Uchida, S. Uchida, S. Fukushima, K. Kataoka, T. Saito, U. Chung, S. Ohba, *Sci. Rep.* **2016**, *6*, 18743.
- [350] P. D. R. C. H. Evans, S. C. Ghivizzani, *J. Cell. Physiol.* **2012**, *227*, 416.
- [351] A. Michael, *Gene Ther.* **1996**, *3*, 1035.

ADVANCED THERAPEUTICS

Reprint Order Form

Wiley-VCH Verlag GmbH & Co. KGaA
Advanced Therapeutics
Boschstr. 12
69469 Weinheim
Germany

Charges for Reprints in Euro (excl. VAT), prices are subject to change. Minimum order 50 copies; single issues for authors at a reduced price.

No. of pages	50 copies	100 copies	150 copies	200 copies	300 copies	500 copies
1–4	345,—	395,—	425,—	445,—	548,—	752,—
5–8	490,—	573,—	608,—	636,—	784,—	1077,—
9–12	640,—	739,—	786,—	824,—	1016,—	1396,—
13–16	780,—	900,—	958,—	1004,—	1237,—	1701,—
17–20	930,—	1070,—	1138,—	1196,—	1489,—	2022,—
every additional 4 pages	147,—	169,—	175,—	188,—	231,—	315,—

Please send me and bill me for

☐ no. of reprints ☐ airmail (+ 25 Euro)
☐ surface mail
☐ Fedex No.: _____

☐ high-resolution PDF file (330 Euro)
E-mail address: _____
☐ Special Offer: _____

If you order 200 or more reprints you will
get a PDF file for half price.

*Please note: It is not permitted to present the PDF file on
the internet or on company homepages.*

Cover Posters (prices excl. VAT)

Posters of published covers are available in two sizes:

☐ DIN A2 42 x 60 cm / 17 x 24in (one copy: 39 Euro)

☐ DIN A1 60 x 84 cm / 24 x 33in (one copy: 49 Euro)

Postage for shipping posters overseas by airmail:
+ 25 Euro

Postage for shipping posters within Europe by surface
mail: + 15 Euro

_____
Date, Signature

Please complete this form and return it via E-Mail to the
Editorial Office at

E-mail: advtherap@wiley.com

Manuscript No.: _____

Customer No.: (if available) _____

Purchase Order No.: _____

Author: _____

Date: _____

Information regarding VAT: Please note that from German sales tax point of view, the charge for Reprints, Issues or Posters is considered as "supply of goods" and therefore, in general, such delivery is a subject to German sales tax. However, this regulation has no impact on customers located outside of the European Union. Deliveries to customers outside the Community are automatically tax-exempt. Deliveries within the Community to institutional customers outside of Germany are exempted from the German tax (VAT) only if the customer provides the supplier with his/her VAT number. The VAT number (value added tax identification number) is a tax registration number used in the countries of the European Union to identify corporate entities doing business there. Starting with a country code (e.g. FR for France), followed by numbers.

VAT number: _____

Mail reprints / copies of the issue to:

_____
_____
_____
_____
_____

Send bill to:

_____
_____
_____
_____
_____

☐ I will pay by bank transfer

☐ I will pay by credit card

VISA, Mastercard and AMERICAN EXPRESS

For your security please use this link (Credit Card
Token Generator) to create a secure code Credit
Card Token and include this number in the form

_____
V _____

instead of the credit card data. Click here:

https://www.wiley-vch.de/editorial_production/index.php

CREDIT CARD TOKEN NUMBER